



Banjo Corporation Chemical Resistance Chart

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	1,2,2,2-Tetrafluoroethane, pure - Hydrocarbon, Aliphatic, Halogenated	D	D	D	D	D	D	D	D
	1,2-ethanediol, 30% - Alcohol, Aliphatic, Polyol	A	D	D	D	D	D	D	D
	1,2-ethanediol, pure - Alcohol, Aliphatic, Polyol	A	D	D	D	D	D	D	D
	1,2-propanediol, pure - Alcohol, Aliphatic, Polyol	A	D	D	D	D	D	D	D
	1,3-Benzenediol, 5% - Alcohol, Aromatic, Polyol	A	D	D	D	D	D	D	D
	1,3-Benzenediol, pure - Alcohol, Aromatic, Polyol	A	D	D	D	D	D	D	D
	1,3-Benzenediol, saturated - Alcohol, Aromatic, Polyol	A	D	D	D	D	D	D	D
	1,3-Butylene Glycol, pure - Alcohol, Aliphatic, Polyol	D	D	D	D	D	D	D	D
	1,4-benzoquinone, pure - Ketone, Aliphatic, Cyclic	D	D	D	D	D	D	D	D
	1-Dodecanol, pure - Alcohol, Aliphatic	D	D	D	D	D	D	D	D
	1-Hexadecanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	1-Propanol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	1-Propanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	2-(2-Ethoxyethoxy)ethanol, pure - Ether, Aliphatic, Alcohol	A	D	D	D	D	D	D	D
	2,4,6-Trimethyl-1,3,5-trioxane, pure - Ketone, Aliphatic, Cyclic	D	D	D	D	D	D	D	D
	2-Butoxyethanol, pure - Ether, Aliphatic, Alcohol	D	D	D	D	D	D	D	D
	2-Mercaptoethanol, pure - Alcohol, Aliphatic, Mercaptan	D	D	D	D	D	D	D	D
	2-Methoxyethanol Acetate, pure - Ether, Aliphatic, Ester	C	D	D	D	D	D	D	D
	2-Methoxyethanol, pure - Ether, Aliphatic, Alcohol	B	D	D	D	D	D	D	D
	2-Propanol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	2-Propanol, 30% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	2-Propanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	3-Pentanone, pure - Ketone, Aliphatic	B	D	D	D	D	D	D	D
	4-Hydroxy-4-methyl-2-pentanone, pure - Ketone, Aliphatic, Alcohol	A	D	D	D	D	D	D	D
	Abietic Acid	D	D	D	D	D	D	D	D
	Acetaldehyde	B	A	A	A	A	C	C	C
	Acetamide	A	D	D	D	D	A	C	A
	Acetanilide	D	D	D	D	D	A	C	C
	Acetic Acid, <5% - Acid, Organic	A	A	A	A	D	A	A	D
	Acetic Acid, 1% - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, 10% - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, 100% - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, 25% - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, 30%	A	D	D	D	D	A	D	D
	Acetic Acid, 5%	A	D	D	D	D	A	A	B
	Acetic Acid, 50% - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, 60% - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, 90% - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, Glacial	A	B	A	A	D	D	C	C
	Acetic Acid, Glacial - Acid, Organic	A	D	D	D	D	D	D	D
	Acetic Acid, Hot, High Pressure	D	D	D	D	D	C	C	C
	Acetic Anhydride	B	A	A	A	A	C	C	C
	Acetoacetic Acid	D	D	D	D	D	A	C	C
	Acetone	B	A	A	A	A	A	C	C
	Acetone Cyanohydrin	D	D	D	D	D	A	C	C
	Acetonitrile	A	D	D	D	D	A	A	C
	Acetophenetidine	D	D	D	D	D	C	A	B
	Acetophenone	C	D	D	D	D	A	C	C
	Acetotoluidide	D	D	D	D	D	C	A	B
	Acetyl Acetone	D	D	D	D	D	A	C	C
	Acetyl Bromide	D	D	D	D	D	A	A	C
	Acetyl Chloride	D	D	D	D	D	C	A	C
	Acetylene	C	A	A	A	A	A	A	A
	Acetylene Tetrabromide	D	D	D	D	D	A	A	C
	Acetylene Tetrachloride	D	D	D	D	D	A	A	C
	Acetylsalicylic Acid	D	D	D	D	D	C	A	B
	Acidic Cleaning Solution - Detergent	D	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
Acids, Non-organic		D	D	D	D	D	D	D	D
Acids, Organic		D	D	D	D	D	D	D	D
Aconitic Acid		D	D	D	D	D	D	D	D
Acridine		D	D	D	D	D	D	D	D
Acrolein		D	D	D	D	D	A	C	C
Acrylamide, pure - Misc.		A	D	D	D	D	D	D	D
Acrylic Acid		D	A	A	A	D	C	D	B
Acrylonitrile		C	B	A	A	D	C	C	C
Adipic Acid		A	B	A	A	D	A	D	A
Aero Lubriplate		D	D	D	D	D	C	A	A
Aero Shell 17 Grease		D	D	D	D	D	C	A	A
Aero Shell 750		D	D	D	D	D	C	A	B
Aero Shell 7A Grease		D	D	D	D	D	C	A	B
Aero Shell IAC		D	D	D	D	D	C	A	A
Aerosafe 2300		D	D	D	D	D	A	C	C
Aerosafe 2300W		D	D	D	D	D	A	C	C
Aerozene 50 (50% Hydrazine 50% UDMH)		D	D	D	D	D	A	C	C
Air Below 200° F		D	D	D	D	D	A	A	B
Air, 200 - 300° F		D	D	D	D	D	B	A	C
Air, 300 - 400° F		D	D	D	D	D	C	A	C
Air, 400 - 500° F		D	D	D	D	D	C	C	C
Alanine, pure - Misc.		A	D	D	D	D	D	D	D
Alconox detergent - Detergent		A	D	D	D	D	D	D	D
Aliphatic Dicarboxylic Acid		D	D	D	D	D	C	A	B
Alkaline Sucrose - Misc.		A	D	D	D	D	D	D	D
Alkanes (Paraffin Hydrocarbons)		D	D	D	D	D	C	A	A
Alkanesulfonic Acid		D	D	D	D	D	C	A	A
Alkazene		D	D	D	D	D	C	B	C
Alkenes (Olefin Hydrocarbons)		D	D	D	D	D	C	A	B
Alkyl Acetone		D	D	D	D	D	A	C	C
Alkyl Alcohol		D	D	D	D	D	C	A	A
Alkyl Amine		D	D	D	D	D	C	A	A
Alkyl Aryl Sulfonates		D	D	D	D	D	C	A	A
Alkyl Aryl Sulfonics		D	D	D	D	D	C	A	A
Alkyl Benzene		D	D	D	D	D	C	A	B
Alkyl Chloride		D	D	D	D	D	C	A	B
Alkyl Sulfide		D	D	D	D	D	C	A	B
Alkyl naphthalene Sulfonic Acid		D	D	D	D	D	C	A	A
Allyl Alcohol, pure - Alcohol, Aliphatic		A	D	D	D	D	D	D	D
Allyl Chloride		D	D	D	D	D	C	A	B
Allylidene Diacetate		D	D	D	D	D	A	C	C
Alpha Picoline		D	D	D	D	D	A	C	C
Alum, 5% - Salt, Inorganic		A	B	A	A	D	A	A	A
Alum, pure - Salt, Inorganic		A	D	D	D	D	D	D	D
Aluminum Acetate		D	D	D	D	D	A	C	B
Aluminum Bromide		D	D	D	D	D	A	A	A
Aluminum Chlorate		D	D	D	D	D	A	C	C
Aluminum Chloride		A	C	A	A	A	A	A	A
Aluminum Ethylate		D	D	D	D	D	D	D	D
Aluminum Fluoride		A	D	D	D	D	A	A	A
Aluminum Fluorosilicate		D	D	D	D	D	D	D	D
Aluminum Formate		D	D	D	D	D	A	C	C
Aluminum Hydroxide		A	D	D	D	D	A	B	B
Aluminum Linoleate		D	D	D	D	D	C	A	A
Aluminum Nitrate		D	D	D	D	D	A	A	A
Aluminum Oxalate		D	D	D	D	D	A	C	C
Aluminum Phosphate		D	D	D	D	D	A	A	A
Aluminum Potassium Sulfate		A	D	D	D	D	A	C	C
Aluminum Salts		A	D	D	D	D	A	A	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Aluminum Sodium Sulfate	D	D	D	D	D	A	C	C
	Aluminum Sulfate	A	C	A	A	A	A	A	A
	Alums-NH3 -Cr -K	D	D	D	D	A	A	C	A
	Ambrex 33 (Mobil)	D	D	D	D	D	C	A	A
	Ambrex 830 (Mobil)	D	D	D	D	D	C	A	A
	Amines-Mixed	D	D	D	D	A	B	C	C
	Amino Acids, pure - Misc.	A	D	D	D	D	D	D	D
	Aminoanthraquinone	D	D	D	D	D	D	D	D
	Aminoazobenzene	D	D	D	D	D	D	D	D
	Aminobenzene Sulfonic Acid	D	D	D	D	D	D	D	D
	Aminobenzoic Acid	D	B	A	A	D	C	C	C
	Aminopyridine	D	D	D	D	D	D	D	D
	Aminosalicic Acid	D	D	D	D	D	D	D	D
	Ammonia (Anhydrous)	D	A	A	A	A	A	C	C
	Ammonia and Lithium Metal in Solution	D	D	D	D	D	B	C	B
	Ammonia, 25% - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Ammonia, Gas, Cold	A	D	D	D	D	A	C	A
	Ammonia, Gas, Hot	D	D	D	D	D	B	C	C
	Ammonia, Liquid (Anhydrous)	D	D	D	D	D	A	C	B
	Ammonium Acetate	A	D	D	D	D	A	C	C
	Ammonium Arsenate	D	D	D	D	D	A	C	C
	Ammonium Benzoate	D	D	D	D	D	A	C	C
	Ammonium Bicarbonate	D	D	D	D	D	A	C	C
	Ammonium Bisulfite	D	D	D	D	D	A	C	C
	Ammonium Bromide	D	D	D	D	D	A	A	A
	Ammonium Carbamate	D	B	A	A	D	A	C	C
	Ammonium Carbonate	A	B	A	A	D	A	A	C
	Ammonium Chloride, 2N	A	D	D	D	A	A	A	A
	Ammonium Citrate	D	D	D	D	D	A	C	C
	Ammonium Dichromate	D	D	D	D	D	A	C	C
	Ammonium Diphosphate	D	D	D	D	D	A	C	C
	Ammonium Fluoride	A	D	D	D	D	A	A	A
	Ammonium Fluorosilicate	D	D	D	D	D	D	D	D
	Ammonium Formate	D	D	D	D	D	A	C	C
	Ammonium Glycolate, pure - Salt, Inorganic, Amine	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 10% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 1N - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 25% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 28% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 3 Molar	A	B	A	A	A	A	C	C
	Ammonium Hydroxide, 30% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 5% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 6% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, 6N - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Hydroxide, Concentrated	A	B	A	A	A	A	C	C
	Ammonium Hydroxide, pure - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Ammonium Iodide	D	D	D	D	D	A	A	A
	Ammonium Lactate	D	D	D	D	D	A	C	C
	Ammonium Metaphosphate	D	D	D	D	D	A	C	C
	Ammonium Molybdenate	D	D	D	D	D	A	C	C
	Ammonium Nitrate, 2N	A	A	A	A	A	A	C	A
	Ammonium Nitrite	D	D	D	D	D	A	D	A
	Ammonium Oxalate	A	D	D	D	D	A	C	C
	Ammonium Perchlorate	D	D	D	D	D	A	C	C
	Ammonium Perchloride	D	D	D	D	D	D	D	D
	Ammonium Persulfate 10%	D	D	D	D	D	A	D	C
	Ammonium Persulfate Solution	A	D	D	D	D	A	D	C
	Ammonium Phosphate	A	B	A	A	D	A	C	A
	Ammonium Phosphate, Dibasic	D	D	D	D	A	A	D	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Ammonium Phosphate, Mono-Basic	D	D	D	D	A	A	D	A
	Ammonium Phosphate, Tribasic	D	D	D	D	A	A	D	A
	Ammonium Phosphite	D	D	D	D	D	A	C	C
	Ammonium Picrate	D	D	D	D	D	A	C	C
	Ammonium Polysulfide	D	D	D	D	D	A	C	C
	Ammonium Salicylate	D	D	D	D	D	A	C	C
	Ammonium Salts	A	D	D	D	D	A	C	A
	Ammonium Sulfamate	D	D	D	D	D	A	C	C
	Ammonium Sulfate	A	B	A	A	A	A	C	A
	Ammonium Sulfate Nitrate	D	D	D	D	D	A	C	A
	Ammonium Sulfide	A	D	D	D	D	A	C	A
	Ammonium Sulfite	D	D	D	D	D	A	C	C
	Ammonium Thiocyanate	D	D	D	D	D	A	C	C
	Ammonium Thioglycolate	D	D	D	D	D	A	C	C
	Ammonium Thiosulfate	D	D	D	D	D	A	C	C
	Ammonium Tungstate	D	D	D	D	D	A	C	C
	Ammonium Valerate	D	D	D	D	D	A	C	C
	Amyl Acetate	B	D	D	D	A	C	C	A
	Amyl Alcohol	A	A	A	A	A	A	C	C
	Amyl Borate	D	D	D	D	D	C	A	A
	Amyl Butyrate	D	D	D	D	D	C	A	A
	Amyl Chloride	C	D	D	D	A	C	A	D
	Amyl Chloronaphthalene	D	D	D	D	D	C	A	C
	Amyl Cinnamic Aldehyde	D	D	D	D	D	C	A	B
	Amyl Laurate	D	D	D	D	D	C	A	B
	Amyl Mercaptan	D	D	D	D	D	C	A	B
	Amyl Naphthalene	D	D	D	D	D	C	A	C
	Amyl Nitrate	D	D	D	D	D	A	C	C
	Amyl Nitrite	D	D	D	D	D	A	C	C
	Amyl Phenol	D	D	D	D	D	D	D	D
	Amyl Propionate	D	D	D	D	D	C	A	A
	Anderol, L- 826 (di-ester)	D	D	D	D	D	C	A	B
	Anderol, L- 829 (di-ester)	D	D	D	D	D	C	A	B
	Anderol, L-774 (di-ester)	D	D	D	D	D	C	A	B
	ANG-25 (Di-ester Base) (TG749)	D	D	D	D	D	C	A	B
	ANG-25 (Glycerol Ester)	D	D	D	D	D	A	A	B
	Aniline	A	A	A	A	A	C	C	C
	Aniline Dyes	D	A	A	A	A	C	C	C
	Aniline Hydrochloride	D	D	D	D	D	B	B	B
	Aniline Hydrochloride	D	D	D	D	D	A	C	C
	Aniline Oil	D	D	D	D	D	B	C	C
	Aniline Sulfate	D	D	D	D	D	A	C	C
	Aniline Sulfite	D	D	D	D	D	A	C	C
	Animal Fats	D	D	D	D	D	B	A	A
	Animal Oil (Lard Oil)	D	D	D	D	A	B	A	A
	Anisole	D	D	D	D	D	D	D	D
	Anisoyl Chloride	D	D	D	D	D	D	D	D
	AN-O-3 Grade M	D	D	D	D	D	C	A	A
	AN-O-366	D	D	D	D	D	C	A	A
	AN-O-6	D	D	D	D	D	C	A	A
	Ansul Ether 161 or 181	D	D	D	D	D	C	C	C
	Anthracene	D	D	D	D	D	C	A	B
	Anthranilic Acid	D	D	D	D	D	D	D	D
	Anthraquinone	D	D	D	D	D	D	D	D
	Anti-freeze Solutions	D	D	D	D	D	A	C	C
	Antimony Chloride	D	D	D	D	D	C	A	A
	Antimony Pentachloride	D	D	D	D	D	C	A	A
	Antimony Pentafluoride	D	D	D	D	D	D	D	D
	Antimony Sulfate	D	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Antimony Tribromide	D	D	D	D	D	C	A	A
	Antimony Trichloride	D	D	D	D	D	C	A	A
	Antimony Trifluoride	D	D	D	D	D	C	A	A
	Antimony Trioxide	D	D	D	D	D	C	A	A
	AN-VV-O-366b Hydr. Fluid	D	D	D	D	D	C	A	A
	Aqua Regia	C	C	C	A	D	C	C	C
	Arachidic Acid	D	D	D	D	D	D	D	D
	Argon	D	D	D	D	D	A	A	A
	Aroclor, 1248	D	A	A	A	D	C	A	C
	Aroclor, 1254	D	D	D	D	D	B	A	C
	Aroclor, 1260	D	D	D	D	D	D	A	A
	Aromatic Fuel -50%	D	D	D	D	D	C	A	B
	Arsenic Acid	A	B	A	A	A	A	A	A
	Arsenic Oxide	D	D	D	D	D	D	D	D
	Arsenic Trichloride	D	D	D	D	D	C	C	A
	Arsenic Trioxide	D	B	A	A	D	D	D	A
	Arsenic Trisulfide	D	D	D	D	D	C	C	A
	Arsenites	D	D	D	D	D	D	D	D
	Arsine	D	D	D	D	D	D	D	D
	Aryl Orthosilicate	D	D	D	D	D	D	D	D
	Ascorbic Acid	D	A	A	A	D	D	C	C
	Askarel Transformer Oil	D	D	D	D	D	C	A	B
	Aspartic Acid	D	D	D	D	D	A	C	C
	Asphalt	D	A	A	A	A	C	A	B
	ASTM Oil, No.1	D	D	D	D	D	C	A	A
	ASTM Oil, No.2	D	D	D	D	D	C	A	A
	ASTM Oil, No.3	D	D	D	D	D	C	A	A
	ASTM Oil, No.4	D	D	D	D	D	C	A	B
	ASTM Oil, No.5	D	D	D	D	D	C	A	A
	ASTM Reference Fuel A	D	D	D	D	D	C	A	A
	ASTM Reference Fuel B	D	D	D	D	D	C	A	A
	ASTM Reference Fuel C	D	D	D	D	D	C	A	B
	ASTM Reference Fuel D	D	D	D	D	D	C	A	B
	Asymmetrical Trimethylbenzene, pure - Hydrocarbon, Aromatic	C	D	D	D	D	D	D	D
	ATL-857	D	D	D	D	D	C	A	B
	Atlantic Dominion F	D	D	D	D	D	C	A	A
	Atlantic Utro Gear-e	D	D	D	D	D	C	A	A
	Atlantic Utro Gear-EP Lube.	D	D	D	D	D	C	A	A
	Aure 903R (Mobil)	D	D	D	D	D	C	A	A
	AUREX 256	D	D	D	D	D	D	D	D
	Automatic Transmission Fluid	D	D	D	D	D	C	A	A
	Automotive Brake Fluid	D	D	D	D	D	A	C	C
	AXAREL 9100	D	D	D	D	D	D	D	D
	Azobenzene	D	D	D	D	D	D	D	D
	Bardol B	D	D	D	D	D	C	A	C
	Barium Carbonate	D	D	D	D	D	A	C	C
	Barium Chlorate	D	D	D	D	D	A	C	C
	Barium Chloride	D	B	A	A	D	A	A	A
	Barium Cyanide	D	D	D	D	A	A	A	A
	Barium Hydroxide	D	A	A	A	A	A	A	A
	Barium Iodide	D	D	D	D	D	A	A	A
	Barium Nitrate	D	B	A	A	D	A	C	C
	Barium Oxide	D	D	D	D	D	A	A	A
	Barium Peroxide	D	D	D	D	D	A	C	C
	Barium Polysulfide	D	D	D	D	D	A	C	C
	Barium Salts	A	D	D	D	D	A	A	A
	Barium Sulfate	D	B	A	A	D	A	A	A
	Barium Sulfide	D	D	D	D	A	A	A	A
	Bayol 35	D	D	D	D	D	C	A	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
Bayol D		D	D	D	D	D	C	A	A
Beer		A	A	A	A	A	A	A	A
Beet Sugar Liquids		D	D	D	D	D	A	A	A
Beet Sugar Liquors		D	D	D	D	A	A	A	A
Benzaldehyde		A	D	D	D	A	A	C	C
Benzaldehyde Disulfonic Acid		D	D	D	D	D	D	D	D
Benzamide		D	D	D	D	D	C	A	B
Benzanthrone		D	D	D	D	D	C	A	B
Benzenamine, pure - Amine, Aromatic		A	D	D	D	D	D	D	D
Benzene		C	B	A	A	A	C	A	C
Benzene Hexachloride		D	D	D	D	D	D	D	D
Benzenesulfonic Acid 10%		D	D	D	D	D	C	A	C
Benzenesulfonic Acid, pure - Acid, Organic, Aromatic		A	D	D	D	D	D	D	D
Benzidine		D	D	D	D	D	C	A	B
Benzidine 3 Sulfonic Acid		D	D	D	D	D	C	A	B
Benzil		D	D	D	D	D	C	A	B
Benzilic Acid		D	D	D	D	D	C	A	B
Benzine (Ligroin)		D	D	D	D	D	C	A	A
Benzocatechol		D	D	D	D	D	C	A	B
Benzochloride		D	D	D	D	D	A	A	C
Benzoic Acid		A	B	A	A	A	C	A	C
Benzoin		D	D	D	D	D	C	A	B
Benzonitrile		D	D	D	D	D	A	C	C
Benzophenone		D	D	D	D	D	B	A	D
Benzoquinone		D	D	D	D	D	B	A	D
Benzotrichloride		D	D	D	D	D	A	A	C
Benzotrifluoride		D	D	D	D	D	A	A	C
Benzoyl Chloride		D	D	D	D	D	D	A	D
Benzoyl Peroxide		D	D	D	D	D	D	D	D
Benzoylsulfonic Acid		D	D	D	D	D	C	A	B
Benzyl Acetate		D	D	D	D	D	A	C	C
Benzyl Acetate, pure - Ester, Aromatic		A	D	D	D	D	D	D	D
Benzyl Alcohol		B	D	D	D	D	B	A	C
Benzyl Amine		D	D	D	D	D	D	D	D
Benzyl Benzoate		D	D	D	D	D	C	A	C
Benzyl Bromide		D	D	D	D	D	C	A	C
Benzyl Butyl Phthalate		D	D	D	D	D	A	C	C
Benzyl Carbinol, pure - Alcohol, Aromatic		D	D	D	D	D	D	D	D
Benzyl Chloride		B	D	D	D	D	C	A	C
Benzyl Phenol		D	D	D	D	D	C	A	B
Benzyl Salicylate		D	D	D	D	D	C	A	B
Beryllium Chloride		D	D	D	D	D	A	A	A
Beryllium Fluoride		D	D	D	D	D	A	A	A
Beryllium Oxide		D	D	D	D	D	A	A	A
Beryllium Sulfate		D	D	D	D	D	A	C	C
beta-Mercaptoethanol, pure - Alcohol, Aliphatic, Mercaptan		D	D	D	D	D	D	D	D
Bis(2-ethylhexyl) Phthalate, pure - Ester, Aromatic		B	D	D	D	D	D	D	D
Bismuth Carbonate		D	D	D	D	D	A	C	C
Bismuth Nitrate		D	D	D	D	D	A	C	C
Bismuth Oxychloride		D	D	D	D	D	A	C	C
Bittern		D	D	D	D	D	D	D	D
Black Liquor		D	B	A	A	A	A	D	C
Black Point 77		D	D	D	D	D	A	A	A
Blast Furnace Gas		D	D	D	D	D	C	A	C
Bleach Liquor		D	D	D	D	D	A	A	C
Bleach Solutions		C	D	D	D	D	A	A	D
Borax		A	D	D	D	A	A	A	B
Borax Solutions		D	D	D	D	D	A	A	D
Bordeaux Mixture		D	D	D	D	D	A	A	B



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Boric Acid	A	B	A	A	A	A	A	A
	Boric Oxide	D	D	D	D	D	A	C	C
	Borneol	D	D	D	D	D	C	A	B
	Bornyl Acetate	D	D	D	D	D	C	A	B
	Bornyl Chloride	D	D	D	D	D	C	A	B
	Bornyl Formate	D	D	D	D	D	C	A	B
	Boron Fluids (HEF)	D	D	D	D	D	C	A	B
	Boron Hydride	D	D	D	D	D	D	D	D
	Boron Phosphate	D	D	D	D	D	D	D	D
	Boron Tribromide	D	D	D	D	D	D	D	D
	Boron Trichloride	D	D	D	D	D	D	D	D
	Boron Trifluoride	D	D	D	D	D	D	D	D
	Boron Trioxide	D	D	D	D	D	D	D	D
	Brake Fluid DOT3 (Glycol Type)	D	D	D	D	D	A	C	C
	Bray GG-130	D	D	D	D	D	C	A	B
	Brayco 719-R (VV-H-910)	D	D	D	D	D	A	C	C
	Brayco 885 (MIL-L-6085A)	D	D	D	D	D	C	A	B
	Brayco 910	D	D	D	D	D	A	C	B
	Bret 710	D	D	D	D	D	A	C	B
	Brine	A	C	A	A	D	A	A	A
	Brine (Seawater)	D	D	D	D	D	C	A	A
	Brom - 113	D	D	D	D	D	C	D	C
	Brom - 114	D	D	D	D	D	C	B	B
	Bromic Acid	D	D	D	D	D	A	C	C
	Bromine	C	D	D	D	A	C	A	C
	Bromine Pentafluoride	D	D	D	D	D	C	C	C
	Bromine Trifluoride	D	D	D	D	D	C	C	C
	Bromine Water	D	D	D	D	D	B	A	C
	Bromobenzene	C	D	D	D	D	C	A	C
	Bromobenzene Cyanide	D	D	D	D	D	A	C	C
	Bromochloro Trifluoroethane (Halothane)	D	D	D	D	D	C	A	C
	Bromoform	C	D	D	D	D	C	A	B
	Bromomethane (Methyl Bromide)	D	D	D	D	D	C	A	B
	Bromotrifluoroethylene (BFE)	D	D	D	D	D	D	D	D
	Bromotrifluoromethane (F-13B1)	D	D	D	D	D	D	D	D
	Brucine Sulfate	D	D	D	D	D	A	C	C
	Buffered Oxide Etchants	D	D	D	D	D	D	D	D
	Bunker Oil	D	D	D	D	D	C	A	A
	Bunker's C (Fuel Oil)	D	A	A	A	D	C	A	A
	Butadiene (Monomer)	C	A	A	A	A	C	A	C
	Butane	C	A	A	A	A	C	A	A
	Butane, 2, 2-Dimethyl	D	D	D	D	D	C	A	A
	Butane, 2, 3-Dimethyl	D	D	D	D	D	C	A	A
	Butanedial	D	D	D	D	D	A	C	C
	Butanediol, pure - Alcohol, Aliphatic, Polyol	D	D	D	D	D	D	D	D
	Butanol (Butyl Alcohol)	A	D	D	D	A	B	A	A
	Butene 2-Ethyl (1-Butene 2-Ethyl)	D	D	D	D	D	C	A	A
	Butter-Animal Fat	D	D	D	D	D	A	A	A
	Butyl Acetate or n-Butyl Acetate	C	A	A	A	A	C	C	C
	Butyl Acetyl Ricinoleate	D	D	D	D	D	A	A	B
	Butyl Acrylate	D	D	D	D	D	A	C	C
	Butyl Alcohol	A	A	A	A	D	C	A	A
	Butyl Alcohol (Secondary)	D	D	D	D	D	B	A	B
	Butyl Alcohol (Tertiary)	D	D	D	D	D	B	A	B
	Butyl Amine or N-Butyl Amine	D	D	D	D	D	C	C	A
	Butyl Benzoate	D	D	D	D	D	A	C	C
	Butyl Benzoate or n-Butyl Benzoate	D	D	D	D	D	A	A	C
	Butyl Benzolate	D	D	D	D	D	D	D	D
	Butyl Butyrate or n-Butyl Butyrate	D	D	D	D	D	A	A	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Butyl Carbitol	D	D	D	D	D	A	C	C
	Butyl Cellosolve	D	D	D	D	D	B	C	C
	Butyl Cellosolve Acetate	D	D	D	D	D	A	C	C
	Butyl Cellosolve Adipate	D	D	D	D	D	B	B	C
	Butyl Chloride	C	D	D	D	D	C	A	A
	Butyl Ether or n-Butyl Ether	D	D	D	D	D	C	C	C
	Butyl Glycolate	D	D	D	D	D	A	C	C
	Butyl Lactate	D	D	D	D	D	A	C	C
	Butyl Laurate	D	D	D	D	D	A	C	C
	Butyl Mercaptan (Tertiary)	D	D	D	D	D	C	A	C
	Butyl Methacrylate	D	D	D	D	D	A	C	C
	Butyl Oleate	D	D	D	D	D	B	A	C
	Butyl Oxalate	D	D	D	D	D	A	C	C
	Butyl Phthalate, pure - Ester, Aromatic	C	D	D	D	D	D	D	D
	Butyl Stearate	D	D	D	D	D	C	A	B
	Butylbenzoic Acid	D	D	D	D	D	C	A	B
	Butylene	D	D	D	D	A	C	A	B
	Butylene Glycol, pure - Alcohol, Aliphatic, Polyol	D	D	D	D	D	D	D	D
	Butyraldehyde	D	D	D	D	D	B	C	C
	Butyraldehyde, pure - Aldehyde, Aliphatic	D	D	D	D	D	D	D	D
	Butyric Acid	C	B	A	A	A	C	C	C
	Butyric Anhydride	D	D	D	D	D	A	C	C
	Butyrolactone	D	D	D	D	D	A	C	C
	Butyryl Chloride	D	D	D	D	D	C	A	B
	Cadmium Chloride	D	D	D	D	D	A	C	C
	Cadmium Cyanide	D	D	D	D	D	A	C	C
	Cadmium Nitrate	D	D	D	D	D	A	C	C
	Cadmium Oxide	D	D	D	D	D	A	C	C
	Cadmium Sulfate	D	D	D	D	D	A	C	C
	Cadmium Sulfide	D	D	D	D	D	A	C	C
	Calcine Liquors	D	D	D	D	D	A	A	A
	Calcium Acetate	D	D	D	D	D	A	C	B
	Calcium Arsenate	D	D	D	D	D	A	C	C
	Calcium Benzoate	D	D	D	D	D	C	A	B
	Calcium Bicarbonate	D	D	D	D	D	A	C	C
	Calcium Bisulfide	D	D	D	D	D	A	C	C
	Calcium Bisulfite	A	A	A	A	A	A	C	B
	Calcium Bromide	D	D	D	D	D	A	A	A
	Calcium Carbide	D	D	D	D	D	D	D	D
	Calcium Carbonate	D	A	A	A	D	A	A	A
	Calcium Chlorate	D	D	D	D	A	A	C	C
	Calcium Chloride	A	C	A	A	A	A	A	A
	Calcium Chromate	D	D	D	D	D	A	C	C
	Calcium Cyanamide	D	D	D	D	D	D	D	D
	Calcium Cyanide	D	D	D	D	D	A	D	A
	Calcium Fluoride	D	D	D	D	D	A	A	A
	Calcium Gluconate	D	D	D	D	D	A	C	C
	Calcium Hydride	D	D	D	D	D	A	A	A
	Calcium Hydrosulfide	D	D	D	D	D	A	C	C
	Calcium Hydroxide	A	B	A	A	A	A	A	A
	Calcium Hypochlorite	A	C	C	A	A	A	A	B
	Calcium Hypophosphite	D	D	D	D	D	A	C	C
	Calcium Lactate	D	D	D	D	D	A	C	C
	Calcium Naphthenate	D	D	D	D	D	D	D	D
	Calcium Nitrate	D	D	D	D	D	A	A	A
	Calcium Oxalate	D	D	D	D	D	A	C	C
	Calcium Oxide	D	D	D	D	D	A	A	A
	Calcium Permanganate	D	D	D	D	D	D	D	D
	Calcium Peroxide	D	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Calcium Phenolsulfonate	D	D	D	D	D	A	C	C
	Calcium Phosphate	D	D	D	D	D	A	A	A
	Calcium Phosphate Acid	D	D	D	D	D	A	C	C
	Calcium Propionate	D	D	D	D	D	A	C	C
	Calcium Pyridine Sulfonate	D	D	D	D	D	D	D	D
	Calcium Salts	A	D	D	D	D	A	A	A
	Calcium Silicate	D	D	D	D	D	A	A	A
	Calcium Stearate	D	D	D	D	D	C	A	B
	Calcium Sulfamate	D	D	D	D	D	C	A	B
	Calcium Sulfate	D	D	D	D	A	A	C	C
	Calcium Sulfide	D	D	D	D	D	A	A	A
	Calcium Sulfite	D	D	D	D	D	A	A	A
	Calcium Thiocyanate	D	D	D	D	D	A	C	C
	Calcium Thiosulfate	D	D	D	D	D	A	A	B
	Calcium Tungstate	D	D	D	D	D	A	C	C
	Caliche Liquors	D	D	D	D	D	A	A	A
	Camphene	D	D	D	D	D	C	A	B
	Camphor	D	D	D	D	D	C	A	B
	Camphoric Acid	D	D	D	D	D	C	A	B
	Cane Sugar Liquors	D	D	D	D	A	A	A	A
	Capric Acid	D	D	D	D	D	C	A	A
	Caproic Acid	D	D	D	D	D	C	A	A
	Caproic Aldehyde	D	D	D	D	D	B	C	D
	Caprolactam	D	A	A	A	D	C	D	D
	Capronaldehyde	D	D	D	D	D	C	A	A
	Carbamate	D	D	D	D	D	B	A	C
	Carbazole	A	D	D	D	D	D	D	D
	Carbitol	A	D	D	D	D	B	B	B
	Carbolic Acid (Phenol)	D	D	D	D	A	B	A	C
	Carbon Bisulfide	D	D	D	D	A	C	A	C
	Carbon Dioxide	A	A	A	A	A	A	A	A
	Carbon Dioxide (Explosive Decompression Use)	D	D	D	D	D	A	A	A
	Carbon Disulfide	C	D	D	D	D	C	A	C
	Carbon Fluorides	D	D	D	D	D	C	A	B
	Carbon Monoxide	D	A	A	A	D	A	A	A
	Carbon Tetrabromide	D	D	D	D	D	D	D	D
	Carbon Tetrachloride	B	B	A	A	D	C	A	C
	Carbon Tetrafluoride	D	D	D	D	A	C	A	B
	Carbonic Acid	A	D	D	D	A	A	A	B
	Casein	D	D	D	D	D	A	C	C
	Castor Oil	D	A	A	A	D	C	A	A
	Caustic Lime	D	D	D	D	D	A	C	C
	Caustic Potash	A	D	D	D	D	A	C	C
	Caustic Soda (Sodium Hydroxide)	A	D	D	D	A	A	C	C
	Cedarwood Oil, pure - Misc.	C	D	D	D	D	D	D	D
	Cellosolve	B	D	D	D	D	B	C	C
	Cellosolve Butyl	D	D	D	D	D	B	C	C
	Cellosolve, Acetate	C	D	D	D	D	B	C	C
	Celluguard	D	D	D	D	D	A	A	A
	Cellulose Acetate	D	D	D	D	D	A	C	C
	Cellulose Acetate Butyrate	D	D	D	D	D	A	C	C
	Cellulose Ether	D	D	D	D	D	A	C	C
	Cellulose Nitrate	D	D	D	D	D	A	C	C
	Cellulose Tripropionate	D	D	D	D	D	A	C	C
	Cellulube (Phosphate Esters)	D	D	D	D	D	D	D	D
	Cellultherm 2505A	D	D	D	D	D	C	A	B
	Cerium Sulfate	D	D	D	D	D	A	C	C
	Cerous Chloride	D	D	D	D	D	A	C	C
	Cerous Fluoride	D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Cerous Nitrate	D	D	D	D	D	A	C	C
	Cesium Acetate, pure - Salt, Organic	A	D	D	D	D	D	D	D
	Cesium Bromide, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Cesium Chloride, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Cesium Formate, pure - Salt, Organic	A	D	D	D	D	D	D	D
	Cesium Iodide, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Cesium Sulfate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Cesium Trichloroacetate, pure - Salt, Organic, Halogenated	A	D	D	D	D	D	D	D
	Cesium Trifluoroacetate, pure - Salt, Organic, Halogenated	A	D	D	D	D	D	D	D
	Cetane (Hexadecane)	D	D	D	D	D	C	A	A
	Cetyl Alcohol	A	D	D	D	D	C	A	A
	Chaulmoogric Acid	D	D	D	D	D	D	D	D
	China Wood Oil (Tung Oil)	D	D	D	D	D	C	A	A
	Chloral	D	D	D	D	D	A	C	C
	Chloramine	D	D	D	D	D	D	D	D
	Chloranthraquinone	D	D	D	D	D	C	A	B
	Chlordane	D	D	D	D	D	C	A	B
	Chlorextol	D	D	D	D	D	C	A	B
	Chloric Acid	D	D	D	D	D	A	C	C
	Chlorinated Solvents, Dry	D	D	D	D	D	C	A	C
	Chlorinated Solvents, Wet	D	D	D	D	D	C	A	C
	Chlorine (Dry)	C	D	D	D	D	C	A	B
	Chlorine (Plasma)	D	D	D	D	D	D	D	D
	Chlorine (Wet)	C	C	A	A	D	C	C	C
	Chlorine Dioxide	D	C	A	A	D	C	A	C
	Chlorine Dioxide, 8% Cl as NaClO2 in solution	D	D	D	D	D	C	A	C
	Chlorine Trifluoride	D	D	D	D	D	C	C	C
	Chlorine Water	D	D	D	D	D	B	A	C
	Chlorine, Dry	D	D	D	D	A	D	B	C
	Chlorine, Wet	D	D	D	D	A	D	B	C
	Chloro 1-Nitro Ethane (1-Chloro 1-Nitro Ethane)	D	D	D	D	D	C	C	C
	Chloro Oxyfluorides	D	D	D	D	D	D	D	D
	Chloro Xylenols	D	D	D	D	D	C	A	B
	Chloroacetaldehyde	D	D	D	D	D	A	C	C
	Chloroacetic Acid	A	C	A	A	D	C	C	C
	Chloroacetone	D	D	D	D	D	A	C	C
	Chloroacetyl Chloride	D	D	D	D	D	D	D	D
	Chloroamino Benzoic Acid	D	D	D	D	D	A	C	C
	Chloroaniline	D	D	D	D	D	A	C	C
	Chlorobenzaldehyde	D	D	D	D	D	A	C	C
	Chlorobenzene	C	C	A	A	A	C	A	C
	Chlorobenzene (Mono)	D	D	D	D	D	C	A	C
	Chlorobenzene Chloride	D	D	D	D	D	C	A	B
	Chlorobenzene Trifluoride	D	D	D	D	D	C	A	B
	Chlorobenzochloride	D	D	D	D	D	C	A	B
	Chlorobenzotrifluoride	D	D	D	D	D	C	A	B
	Chlorobromo Methane	D	D	D	D	D	B	A	C
	Chlorobromopropane	D	D	D	D	D	C	A	B
	Chlorobutadiene	D	D	D	D	D	C	A	C
	Chlorobutane (Butyl Chloride)	C	D	D	D	D	C	A	A
	Chlorodifluoromethane, pure - Hydrocarbon, Aliphatic, Halogenated	D	D	D	D	D	D	D	D
	Chlorododecane	D	D	D	D	D	C	A	C
	Chloroethane	C	D	D	D	D	C	A	A
	Chloroethane Sulfonic Acid	D	D	D	D	D	A	C	C
	Chloroethylbenzene	D	D	D	D	D	C	A	B
	Chloroform	C	B	A	A	A	C	A	C
	Chlorohydrin	D	D	D	D	D	A	C	C
	Chloromethyl Benzene, pure - Hydrocarbon, Aromatic, Halogenated	B	D	D	D	D	D	D	D
	Chloronaphthalene or o-Chloronaphthalene	D	D	D	D	D	C	A	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Nlon-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Chloronitrobenzene	D	D	D	D	D	A	C	C
	Chlorophenol or o-Chlorophenol	D	D	D	D	D	C	A	C
	Chloropicrin	D	D	D	D	D	C	A	B
	Chloroprene	D	D	D	D	D	C	A	B
	Chlorosilanes	D	D	D	D	D	D	D	D
	Chlorosulfonic Acid	D	D	D	D	A	C	C	C
	Chlorosulphonic Acid, pure - Acid, Organic, Aromatic, Halogenated	C	D	D	D	D	D	D	D
	Chlorotoluene	D	D	D	D	D	C	A	C
	Chlorotoluene Sulfonic Acid	D	D	D	D	D	A	C	C
	Chlorotoluene, pure - Hydrocarbon, Aromatic, Halogenated	B	D	D	D	D	D	D	D
	Chlorotoluidine	D	D	D	D	D	C	A	B
	Chlorotrifluoroethylene (CTFE)	D	D	D	D	D	D	D	D
	Chlorox	D	D	D	D	D	B	A	B
	Chloroxylols	D	D	D	D	D	D	D	D
	Cholesterol	D	D	D	D	D	C	A	B
	Chrome Alum	D	D	D	D	A	A	A	A
	Chrome Plating Solutions	D	D	D	D	D	B	A	C
	Chromic Acid	C	D	D	D	A	B	A	C
	Chromic Chloride	D	D	D	D	D	D	D	D
	Chromic Fluorides	D	D	D	D	D	D	D	D
	Chromic Hydroxide	D	D	D	D	D	D	D	D
	Chromic Nitrates	D	D	D	D	D	D	D	D
	Chromic Oxide	D	D	D	D	D	B	A	C
	Chromic Phosphate	D	D	D	D	D	D	D	D
	Chromic Sulfate	D	D	D	D	D	D	D	D
	Chromic:Surfuric Acid Mixture, 96% - Acid, Inorganic, Oxidizer	C	D	D	D	D	D	D	D
	Chromium Potassium Sulfate (Alum)	D	D	D	D	D	B	A	B
	Chromyl Chlorides	D	D	D	D	D	D	D	D
	Cinnamic Acid	D	D	D	D	D	C	A	B
	Cinnamic Alcohol	D	D	D	D	D	C	A	B
	Cinnamic Aldehyde	D	D	D	D	D	C	A	B
	Cinnamon Oil, pure - Misc.	C	D	D	D	D	D	D	D
	Circo Light Process Oil	D	D	D	D	D	C	A	A
	Citric Acid	A	B	A	A	A	A	A	A
	City Service #65 #120 #250	D	D	D	D	D	C	A	A
	City Service Koolmoter-AP Gear Oil 140-EP lube	D	D	D	D	D	C	A	A
	City Service Pacemaker #2	D	D	D	D	D	C	A	A
	Clorox	D	D	D	D	D	B	A	B
	Coal Tar	D	A	A	A	D	C	A	A
	Cobalt Chloride	D	D	D	D	D	A	A	A
	Cobalt Chloride, 2N	D	D	D	D	D	A	A	A
	Cobaltous Acetate	D	D	D	D	D	A	C	C
	Cobaltous Bromide	D	D	D	D	D	A	A	A
	Cobaltous Linoleate	D	D	D	D	D	D	D	D
	Cobaltous Naphthenate	D	D	D	D	D	D	D	D
	Cobaltous Sulfate	D	D	D	D	D	A	C	C
	Coconut Oil	D	D	D	D	D	C	A	A
	Cod Liver Oil	D	D	D	D	D	A	A	A
	Codeine	D	D	D	D	D	C	A	B
	Coffee	D	D	D	D	A	A	A	A
	Coke Oven Gas	D	D	D	D	A	C	A	C
	Coliche Liquors	D	D	D	D	D	B	D	B
	Convelex 10	D	D	D	D	D	D	D	C
	Coolanol 20 25R 35R 40& 45A (Monsanto)	D	D	D	D	D	C	A	A
	Copper Acetate	D	B	A	A	A	A	C	B
	Copper Ammonium Acetate	D	A	A	A	D	A	C	C
	Copper Carbonate	D	D	D	D	D	A	C	C
	Copper Chloride	D	C	A	A	A	A	A	A
	Copper Cyanide	D	B	A	A	D	A	A	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
Copper Gluconate		D	D	D	D	D	A	C	C
Copper Naphthenate		D	D	D	D	D	D	D	D
Copper Nitrate		D	B	A	A	D	A	D	B
Copper Oxide		D	D	D	D	D	A	A	A
Copper Salts		A	D	D	D	D	A	A	A
Copper Sulfate		D	D	D	D	A	A	A	A
Copper Sulfate 10%		D	B	A	A	D	A	A	A
Copper Sulfate 50%		D	B	A	A	D	A	A	A
Corn Oil		D	A	A	A	D	C	A	A
Cottonseed Oil		A	A	A	A	A	C	A	A
Creosote, Coal Tar		D	B	A	A	A	C	A	A
Creosote, Wood		D	D	D	D	A	C	A	A
Cresol (Methyl Phenol)		B	D	D	D	D	D	A	D
Cresols		D	D	D	D	D	C	B	C
Cresylic Acid		D	B	A	A	A	C	A	C
Crotonaldehyde		D	D	D	D	D	C	A	B
Crotonic Acid		D	D	D	D	D	C	A	B
Crude Oil		D	A	A	A	D	C	A	B
Culture Media - Misc.		A	D	D	D	D	D	D	D
Cumaldehyde		D	D	D	D	D	C	A	B
Cumene		C	B	A	A	D	C	A	C
Cumene Hydroperoxide		D	D	D	D	D	D	D	D
Cupric Sulfate		D	D	D	D	D	B	A	B
Cutting Oil		D	A	A	A	D	C	A	A
Cyanamide		D	D	D	D	D	D	D	D
Cyanides		D	D	D	D	D	D	D	D
Cyanogen Chloride		D	D	D	D	D	D	D	D
Cyanogen Gas		D	D	D	D	D	D	D	D
Cyanohydrin		D	D	D	D	D	D	D	D
Cyanuric Chloride		D	D	D	D	D	D	D	D
Cyclohexane		D	B	A	A	D	C	A	A
Cyclohexanol		A	A	A	A	D	C	A	A
Cyclohexanone		C	B	A	A	D	C	C	C
Cyclohexene		B	D	D	D	D	C	A	B
Cyclohexylamine		D	D	D	D	D	C	A	A
Cyclohexylamine Carbonate		D	D	D	D	D	D	D	D
Cyclohexylamine Laurate		D	D	D	D	D	C	A	A
Cyclopentadiene		D	D	D	D	D	C	A	B
Cyclopentane		C	D	D	D	D	C	A	A
Cyclopolyolefins		D	D	D	D	D	C	A	A
Cymene or p-Cymene		D	D	D	D	D	C	A	C
DDT (Dichlorodiphenyltrichloroethane)		D	D	D	D	D	C	A	B
Decahydronaphthalene, pure - Hydrocarbon, Aromatic		C	D	D	D	D	D	D	D
Decalin		C	D	D	D	D	C	A	C
Decane		C	D	D	D	D	C	A	A
Delco Brake Fluid		D	D	D	D	D	A	C	C
Denatured Alcohol		D	D	D	D	D	A	A	A
Deoxycholate, pure - Detergent		D	D	D	D	D	D	D	D
DEPC, pure - Misc.		A	D	D	D	D	D	D	D
Detergent, Water Solution		A	D	D	D	D	A	A	A
Developing Fluids (Photo)		D	D	D	D	D	B	A	A
Dexron		D	D	D	D	D	C	A	A
Dextran Sulfate, pure - Misc., Sugar		A	D	D	D	D	D	D	D
Dextran, pure - Misc., Sugar		A	D	D	D	D	D	D	D
Dextrin		D	D	D	D	D	C	A	A
Dextro Lactic Acid		D	D	D	D	D	A	C	C
Dextron		D	D	D	D	D	C	A	A
Dextrose		D	A	A	A	D	A	D	D
DI Water		A	D	D	D	D	A	B	B



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Diacetone	B	D	D	D	D	A	C	C
	Diacetone Alcohol	B	A	A	A	A	A	C	C
	Dialkyl Sulfates	D	D	D	D	D	A	C	C
	Diallyl Ether	D	D	D	D	D	D	D	D
	Diallyl Phthalate	D	D	D	D	D	D	D	D
	Diamylamine	D	D	D	D	D	C	A	A
	Diazinon	D	D	D	D	D	C	B	C
	Diazo Salts - Misc., Salts	D	D	D	D	D	D	D	D
	Dibasic Potassium Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Dibasic Sodium Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Dibenzopyrrole, pure - Hydrocarbon, Aromatic, Heterocyclic	A	D	D	D	D	D	D	D
	Dibenzyl (sym-Diphenylethane)	D	D	D	D	D	C	A	B
	Dibenzyl Ether	D	D	D	D	D	B	C	C
	Dibenzyl Sebacate	D	D	D	D	D	B	B	C
	Diborane	D	D	D	D	D	D	D	D
	Dibromoethane	D	D	D	D	D	C	A	B
	Dibromoethyl Benzene	D	D	D	D	D	C	A	C
	Dibutyl Cellosolve Adipate	D	D	D	D	D	A	C	C
	Dibutyl Ether	D	A	A	A	D	C	C	C
	Dibutyl Methyleneidithio Glycolate	D	D	D	D	D	C	A	B
	Dibutyl Phthalate	B	A	A	A	D	C	C	C
	Dibutyl Sebacate	D	D	D	D	D	B	B	C
	Dibutyl Thioglycolate	D	D	D	D	D	C	A	B
	Dibutyl Thiourea	D	D	D	D	D	C	A	B
	Dibutylamine	D	A	A	A	D	D	C	C
	Dichloroacetic Acid	D	D	D	D	D	C	A	B
	Dichloroaniline	D	D	D	D	D	A	C	C
	Dichlorobenzene or o-Dichlorobenzene	C	D	D	D	D	C	A	C
	Dichlorobenzene or p-Dichlorobenzene	C	D	D	D	D	C	A	C
	Dichlorobutane	D	D	D	D	D	C	A	B
	Dichlorobutene	D	D	D	D	D	C	A	B
	Dichlorodifluoromethane, pure - Hydrocarbon, Aliphatic, Halogenated	A	D	D	D	D	D	D	D
	Dichlorodiphenyl-Dichloroethane (DDD)	D	D	D	D	D	C	A	B
	Dichloroethane	C	A	A	A	D	C	A	B
	Dichloroethylene	A	B	A	A	D	C	A	B
	Dichlorohydrin	D	B	A	A	D	A	C	C
	Dichloroisopropyl Ether	D	D	D	D	D	C	C	C
	Dichloromethane	D	D	D	D	D	C	A	B
	Dichlorophenol	C	D	D	D	D	C	A	B
	Dichlorophenoxyacetic Acid	D	D	D	D	D	C	A	B
	Dichloropropane	D	D	D	D	D	C	A	B
	Dichloropropene	D	D	D	D	D	C	A	B
	Dichlorosilane	D	D	D	D	D	D	D	D
	Dicyclohexylamine	D	D	D	D	D	C	C	A
	Dicyclohexylammonium Nitrate	D	D	D	D	D	A	C	C
	Dieldrin	D	D	D	D	D	C	A	B
	Diesel Oil	D	A	A	A	D	C	A	A
	Di-ester Lubricant MIL-L-7808	D	D	D	D	D	C	A	B
	Di-ester Synthetic Lubricants	D	D	D	D	D	C	A	B
	Diethanolamine (DEA)	A	D	D	D	D	A	C	C
	Diethyl Acetamide, pure - Amine, Aliphatic	D	D	D	D	D	D	D	D
	Diethyl Benzene	C	D	D	D	D	D	A	D
	Diethyl Carbonate	D	A	A	A	D	D	D	C
	Diethyl Ether	C	A	A	A	D	C	C	C
	Diethyl Ketone, pure - Ketone, Aliphatic	B	D	D	D	D	D	D	D
	Diethyl Malonate, pure - Ester, Aliphatic	A	D	D	D	D	D	D	D
	Diethyl Phthalate	D	D	D	D	D	C	A	B
	Diethyl Sebacate	D	D	D	D	D	B	B	B
	Diethyl Sulfate	D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Diethylacetamide, pure - Amine, Aliphatic	D	D	D	D	D	D	D	D
	Diethylamine	D	A	A	A	A	D	C	B
	Diethylamine, pure - Amine, Aliphatic	B	D	D	D	D	D	D	D
	Diethylaniline	D	D	D	D	D	A	C	C
	Diethylene Dioxide, pure - Ether, Cyclic	C	D	D	D	D	D	D	D
	Diethylene Glycol	A	A	A	A	D	A	A	A
	Diethylenetriamine	D	A	A	A	D	C	C	D
	Diethylpyrocarbonate, pure - Misc.	A	D	D	D	D	D	D	D
	Difluorodibromomethane	D	D	D	D	D	B	D	C
	Difluoroethane	D	D	D	D	D	C	A	B
	Difluoromonochloroethane	D	D	D	D	D	C	A	B
	Diglycol Chloroformate	D	D	D	D	D	A	C	C
	Diglycolic Acid	D	D	D	D	D	A	C	C
	Dihydroxydiphenylsulfone	D	D	D	D	D	A	C	C
	Diisobutyl Ketone	D	A	A	A	D	A	C	D
	Diisobutylcarbinol	D	D	D	D	D	C	A	A
	Diisobutylene	D	D	D	D	D	C	A	B
	Diisooctyl Sebacate	D	D	D	D	D	C	B	C
	Diisopropyl Ether (DIPE)	D	D	D	D	D	D	D	D
	Diisopropyl Ketone	D	A	A	A	D	A	C	C
	Diisopropylbenzene	D	D	D	D	D	C	A	B
	Diisopropylidene Acetone	D	D	D	D	D	C	A	B
	Dimethyl Acetamide	A	D	D	D	D	A	C	C
	Dimethyl Aniline (Xylidine)	D	D	D	D	D	C	A	B
	Dimethyl Disulfide (DMDS)	D	D	D	D	D	C	A	A
	Dimethyl Ether	D	D	D	D	D	B	B	A
	Dimethyl Formaldehyde	D	D	D	D	D	A	C	C
	Dimethyl Formamide (DMF)	A	A	A	A	D	A	C	C
	Dimethyl Hydrazine	D	A	A	A	D	A	C	C
	Dimethyl Phenyl Carbinol	D	D	D	D	D	C	A	B
	Dimethyl Phenyl Methanol	D	D	D	D	D	C	A	B
	Dimethyl Phthalate	A	D	D	D	D	B	B	C
	Dimethyl Sulfoxide (DMSO)	A	D	D	D	D	A	C	C
	Dimethyl Terephthalate (DMT)	D	A	A	A	D	C	D	C
	Dimethylamine (DMA)	B	A	A	A	D	D	C	C
	Dinitrochlorobenzene	D	A	A	A	D	C	D	C
	Dinitrogen Tetroxide	D	D	D	D	D	D	D	D
	Dinitrotoluene (DNT)	D	D	D	D	D	C	C	C
	Diocetyl Phthalate	B	A	A	A	D	C	B	C
	Diocetyl Sebacate	D	D	D	D	D	B	B	C
	Diocetylamine	D	D	D	D	D	C	A	A
	Dioxane	C	D	D	D	D	B	C	C
	Dioxolane	D	D	D	D	D	B	C	C
	Dipentene	D	D	D	D	D	C	A	B
	Diphenyl	D	A	A	A	D	C	A	C
	Diphenyl Oxides	D	D	D	D	D	C	A	C
	Diphenylamine (DPA)	A	D	D	D	D	C	A	B
	Diphenylene Oxide	D	D	D	D	D	D	D	D
	Diphenylpropane	D	D	D	D	D	C	A	B
	Dipotassium Hydrogen Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Dipropylene Glycol, pure - Alcohol, Aliphatic, Polyol	A	D	D	D	D	D	D	D
	Disilane	D	D	D	D	D	D	D	D
	Disodium Hydrogen Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Distilled Water, pure - Misc.	A	A	A	A	D	A	A	A
	Di-Tert-Butyl Peroxide	D	D	D	D	D	D	D	D
	DMAC, pure - Amine, Aliphatic	A	D	D	D	D	D	D	D
	DMF, pure - Amine, Aliphatic	A	D	D	D	D	D	D	D
	DMSO, pure - Misc.	A	D	D	D	D	D	D	D
	Dodecyl Alcohol, pure - Alcohol, Aliphatic	D	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
Dodecylbenzene		D	D	D	D	D	C	A	B
Dow Chemical 50-4		D	D	D	D	D	A	C	D
Dow Chemical ET378		D	D	D	D	D	D	D	C
Dow Chemical ET588		D	D	D	D	D	A	C	C
Dow Corning -11		D	D	D	D	D	A	A	B
Dow Corning 1208, 4050, 6620, F-60, xF-60		D	D	D	D	D	A	A	A
Dow Corning -1265 Fluorosilicone Fluid		D	D	D	D	D	A	A	B
Dow Corning -200		D	D	D	D	D	A	A	B
Dow Corning 220		D	D	D	D	D	A	A	A
Dow Corning -3		D	D	D	D	D	A	A	B
Dow Corning -33		D	D	D	D	D	A	A	B
Dow Corning -4		D	D	D	D	D	A	A	B
Dow Corning -44		D	D	D	D	D	A	A	B
Dow Corning -5		D	D	D	D	D	A	A	B
Dow Corning -510		D	D	D	D	D	A	A	B
Dow Corning -55		D	D	D	D	D	A	A	B
Dow Corning -550		D	D	D	D	D	A	A	B
Dow Corning -704		D	D	D	D	D	A	A	B
Dow Corning -705		D	D	D	D	D	A	A	B
Dow Corning -710		D	D	D	D	D	A	A	B
Dow Corning F-61		D	D	D	D	D	A	A	A
Dow Guard		D	D	D	D	D	A	A	A
Dowanol P Mix		D	D	D	D	D	D	D	D
Dowtherm, 209		D	D	D	D	A	A	C	C
Dowtherm, A		D	A	A	A	A	C	A	C
Dowtherm, E		D	D	D	D	A	C	A	C
Drinking Water		A	D	D	D	D	A	A	A
Dry Cleaning Fluids		D	D	D	D	D	C	A	C
DTE 20 Series, Mobil		D	D	D	D	D	C	A	B
DTE named series, Mobil, light-heavy		D	D	D	D	D	C	A	A
EDTA, pure - Misc., Chelator		A	D	D	D	D	D	D	D
Elco 28-EP lubricant		D	D	D	D	D	C	A	A
Epichlorohydrin		D	B	A	A	D	C	C	C
Epoxy Resins		D	D	D	D	D	A	C	D
Erucic Acid		D	D	D	D	D	D	D	D
Esam-6 Fluid		D	D	D	D	D	A	C	D
Esso Fuel 208		D	D	D	D	D	C	A	A
Esso Golden Gasoline		D	D	D	D	D	C	A	B
Esso Motor Oil		D	D	D	D	D	C	A	A
Esso Transmission fluid (Type A)		D	D	D	D	D	C	A	A
Esso WS2812 (MIL-L-7808A)		D	D	D	D	D	C	A	A
Esso XP90-EP lubricant		D	D	D	D	D	C	A	A
Esstic 42, 43		D	D	D	D	D	C	A	A
Ethane		D	A	A	A	D	C	A	A
Ethanol		A	A	A	A	D	A	C	C
Ethanol Amine		D	D	D	D	D	A	C	B
Ethanolamine, pure - Amine, Aliphatic		D	A	A	A	D	C	C	C
Ethers		C	D	D	D	D	A	C	C
Ethoxyethyl Acetate (EGMEEA)		D	D	D	D	D	A	C	C
Ethyl Acetate, pure - Ester, Aliphatic		B	D	D	D	D	D	D	D
Ethyl Acetate-Organic Ester		D	D	D	D	A	B	C	C
Ethyl Acetoacetate		D	D	D	D	D	B	C	C
Ethyl Acrylate		D	D	D	D	A	B	C	C
Ethyl Alcohol		A	A	A	A	A	A	C	C
Ethyl Ammonium Dichloride		D	D	D	D	D	D	D	D
Ethyl Benzene		C	B	A	A	D	C	A	C
Ethyl Benzoate		B	D	D	D	D	C	A	C
Ethyl Bromide		D	A	A	A	D	C	A	C
Ethyl Butyrate, pure - Ester, Aliphatic		B	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Ethyl Cellosolve	D	D	D	D	D	B	C	C
	Ethyl Cellulose	D	B	A	A	D	C	C	C
	Ethyl Chloride	C	A	A	A	A	C	A	A
	Ethyl Chlorocarbonate	D	D	D	D	D	B	A	C
	Ethyl Chloroformate	D	D	D	D	D	B	C	C
	Ethyl Cyanoacetate, pure - Ester, Aliphatic, Cyano	A	D	D	D	D	D	D	D
	Ethyl Digol, pure - Ether, Aliphatic, Polyol	A	D	D	D	D	D	D	D
	Ethyl Ether	C	A	A	A	D	C	C	C
	Ethyl Formate	D	D	D	D	D	B	A	C
	Ethyl Hexanol	D	D	D	D	D	A	A	A
	Ethyl Lactate	A	D	D	D	D	A	C	C
	Ethyl Mercaptan	D	D	D	D	D	D	B	C
	Ethyl Nitrite	D	D	D	D	D	A	C	C
	Ethyl Oxalate	D	D	D	D	D	A	B	C
	Ethyl Pentachlorobenzene	D	D	D	D	D	C	A	C
	Ethyl Pyridine	D	D	D	D	D	C	A	B
	Ethyl Silicate	D	D	D	D	D	A	A	A
	Ethyl Stearate	D	D	D	D	D	C	A	B
	Ethyl Sulfate	D	B	A	A	D	D	C	C
	Ethyl Tertiary Butyl Ether	D	D	D	D	D	D	D	D
	Ethyl Valerate	D	D	D	D	D	C	A	B
	Ethylacrylic Acid	D	D	D	D	D	B	D	C
	Ethylamine	D	D	D	D	D	A	C	C
	Ethylcyclopentane	D	D	D	D	D	C	A	A
	Ethylene	D	A	A	A	D	C	C	D
	Ethylene Chloride	C	D	D	D	D	C	B	C
	Ethylene Chlorohydrin	D	D	D	D	D	B	A	C
	Ethylene Cyanohydrin	D	D	D	D	D	C	A	B
	Ethylene Diamine	A	D	D	D	D	A	C	A
	Ethylene Dibromide	D	D	D	D	D	C	A	C
	Ethylene Dichloride	C	B	A	A	D	C	D	C
	Ethylene Glycol	A	A	A	A	A	A	A	A
	Ethylene Glycol Monobutyl Ether, pure - Ether, Aliphatic, Polyol	D	D	D	D	D	D	D	D
	Ethylene Glycol Monoethyl Ether Acetate, pure - Ether, Aliphatic, Ester	D	D	D	D	D	D	D	D
	Ethylene Glycol Monoethyl Ether, pure - Ether, Aliphatic, Polyol	B	D	D	D	D	D	D	D
	Ethylene Glycol Monomethyl Ether Acetate, pure - Ether, Aliphatic, Ester	C	D	D	D	D	D	D	D
	Ethylene Glycol Monomethyl Ether, pure - Ether, Aliphatic, Polyol	B	D	D	D	D	D	D	D
	Ethylene Hydrochloride	D	D	D	D	D	C	A	C
	Ethylene Nitrate, pure - Misc.	D	D	D	D	D	D	D	D
	Ethylene Oxide	C	B	A	A	A	C	C	C
	Ethylene Oxide, (12%) and Freon 12 (80%)	D	D	D	D	D	B	C	C
	Ethylene Trichloride	D	A	A	A	D	C	A	C
	Ethyleneimine	D	D	D	D	D	D	D	D
	Ethylmorpholine Stannous Octoate (50/50 mix)	D	D	D	D	D	B	C	C
	Ethylmorpholine	D	D	D	D	D	C	A	B
	Ethylsulfuric Acid	D	D	D	D	D	A	C	C
	EtO Gas, pure - Ether, Cyclic	A	D	D	D	D	D	D	D
	EtO Liquid, pure - Ether, Cyclic	C	D	D	D	D	D	D	D
	EtO, 100% - Ether, Cyclic	C	D	D	D	D	D	D	D
	EtO, pure - Ether, Cyclic	C	D	D	D	D	D	D	D
	F-60 Fluid (Dow Corning)	D	D	D	D	D	A	A	A
	F-61 Fluid (Dow Corning)	D	D	D	D	D	A	A	A
	Fatty Acids	A	D	D	D	A	C	A	B
	FC-43 Heptacosofluorotri-butylamine	D	D	D	D	D	A	A	A
	FC75 & FC77 (Fluorocarbon)	D	D	D	D	D	A	B	A
	Ferric Acetate	D	D	D	D	D	A	C	C
	Ferric Ammonium Sulfate	D	D	D	D	D	A	C	C
	Ferric Chloride	A	C	C	A	A	A	A	A
	Ferric Ferrocyanide	D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Ferric Hydroxide	D	B	A	A	D	A	C	C
	Ferric Nitrate	D	B	A	A	A	A	A	A
	Ferric Persulfate	D	D	D	D	D	A	A	A
	Ferric Sulfate	A	D	A	A	D	A	A	A
	Ferrous Ammonium Citrate	D	D	D	D	D	A	C	C
	Ferrous Ammonium Sulfate	D	D	D	D	D	A	C	C
	Ferrous Carbonate	D	D	D	D	D	A	C	C
	Ferrous Chloride	A	C	A	A	A	A	A	C
	Ferrous Iodide	D	D	D	D	D	A	C	C
	Ferrous Sulfate	A	C	A	A	A	A	D	C
	Ferrous Tartrate	D	D	D	D	D	A	C	C
	Ficoll-Hypaque - Misc.	A	D	D	D	D	D	D	D
	Fish Oil	D	D	D	D	A	C	A	B
	Fisher Reagent	D	D	D	D	D	B	D	D
	Fluorides - Salt, Inorganic	A	D	D	D	D	D	D	D
	Fluorinated Cyclic Ethers	D	D	D	D	D	A	D	D
	Fluorine (Gas)	C	D	D	D	D	D	D	D
	Fluorine (Liquid)	D	D	D	D	D	C	B	C
	Fluorobenzene	D	D	D	D	D	C	A	B
	Fluoroboric Acid	D	D	D	D	D	A	D	A
	Fluorocarbon Oils	D	D	D	D	D	A	D	D
	Fluoroform (Trifluoromethane)	D	D	D	D	D	D	D	D
	Fluorolube	D	D	D	D	D	A	B	A
	Fluorophosphoric Acid	D	D	D	D	D	D	D	D
	Fluosilicic Acid	A	C	C	A	A	B	B	A
	Fluosulfonic Acid	D	D	D	D	D	D	D	D
	Formaldehyde	A	A	A	A	A	C	C	C
	Formalin, 10% - Aldehyde, Aliphatic	A	D	D	D	D	D	D	D
	Formalin, 30% - Aldehyde, Aliphatic	A	D	D	D	D	D	D	D
	Formalin, 37% - Aldehyde, Aliphatic	A	D	D	D	D	D	D	D
	Formalin, 40% - Aldehyde, Aliphatic	A	D	D	D	D	D	D	D
	Formalin, 5% - Aldehyde, Aliphatic	A	D	D	D	D	D	D	D
	Formalin, pure - Aldehyde, Aliphatic	A	D	D	D	D	D	D	D
	Formamide	D	B	A	A	D	D	C	C
	Formic Acid	A	C	A	A	A	D	C	C
	Freon, 11	D	A	A	A	A	C	C	C
	Freon, 112	D	A	A	A	A	C	A	C
	Freon, 113	D	A	A	A	A	C	C	A
	Freon, 113 + High and Low Aniline Oil	D	D	D	D	A	D	D	A
	Freon, 114	D	A	A	A	A	D	A	A
	Freon, 114B2	D	D	D	D	A	C	B	B
	Freon, 115, 116	D	A	A	A	A	D	C	A
	Freon, 12	A	A	A	A	A	C	D	C
	Freon, 12 and ASTM Oil #2(50/50 Mixture)	D	D	D	D	A	C	A	B
	Freon, 12 and Suniso 4G(50/50 Mixture)	D	D	D	D	A	C	A	B
	Freon, 123 (Dichlorotrifluoroethane)	D	D	D	D	A	D	D	D
	Freon, 124 (Chlorotetrafluoroethane)	D	D	D	D	A	D	D	D
	Freon, 125 (Pentafluoroethane)	D	D	D	D	A	D	D	D
	Freon, 13	D	A	A	A	A	D	A	A
	Freon, 134a (Tetrafluoroethane)	D	D	D	D	A	A	D	D
	Freon, 13B1	D	D	D	D	A	A	A	A
	Freon, 14	D	A	A	A	A	D	A	A
	Freon, 141b (Dichlorofluoroethane)	D	D	D	D	A	D	D	D
	Freon, 142b	D	D	D	D	A	C	B	B
	Freon, 152a (Difluoroethane)	D	D	D	D	A	D	D	D
	Freon, 21	D	A	A	A	A	C	C	C
	Freon, 218	D	D	D	D	A	A	A	A
	Freon, 22	D	A	A	A	A	C	C	C
	Freon, 22 and ASTM Oil #2(50/50 Mixture)	D	D	D	D	A	C	B	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Freon, 23 (Fluoroform)	D	D	D	D	A	D	D	D
	Freon, 31	D	A	A	A	A	D	C	C
	Freon, 32	D	A	A	A	A	D	C	A
	Freon, 502	D	D	D	D	A	A	B	B
	Freon, BF	D	D	D	D	A	C	A	B
	Freon, C316	D	D	D	D	A	A	A	A
	Freon, C318	D	D	D	D	A	A	B	A
	Freon, K-142b	D	D	D	D	A	A	C	A
	Freon, K-152a	D	D	D	D	A	A	C	A
	Freon, MF	D	D	D	D	A	C	B	B
	Freon, PCA	D	D	D	D	A	C	B	A
	Freon, pure - Hydrocarbon, Aliphatic, Halogenated	A	D	D	D	D	D	D	D
	Freon, TA	D	D	D	D	A	B	C	A
	Freon, TC	D	D	D	D	A	B	A	A
	Freon, TF	A	D	D	D	A	C	B	A
	Freon, TMC	D	D	D	D	A	C	A	B
	Freon, T-P35	D	D	D	D	A	A	A	A
	Freon, T-WD602	D	D	D	D	A	B	A	B
	Fuel Oil, #6	D	A	A	A	A	C	A	B
	Fuel Oil, 1, and 2	D	A	A	A	A	C	A	A
	Fuel Oil, Acidic	D	D	D	D	A	C	A	A
	Fuel Oil, pure - Hydrocarbon, Mixture	A	D	D	D	D	D	D	D
	Fumaric Acid	D	D	D	D	D	B	A	A
	Fuming Sulphuric Acid (20/25% Oleum)	D	D	D	D	D	C	A	C
	Furaldehyde	D	D	D	D	D	B	C	C
	Furan (Furfuran)	D	D	D	D	A	C	A	C
	Furfural (Furfuraldehyde)	C	B	A	A	D	C	C	C
	Furfuraldehyde	C	D	D	D	D	B	C	C
	Furfuryl Alcohol	D	A	A	A	D	C	C	C
	Furoic Acid	D	D	D	D	D	D	D	D
	Furyl Carbinol	D	D	D	D	D	B	D	C
	Fyrquel 150 220 300 550	D	D	D	D	D	A	A	C
	Fyrquel 90, 100, 500	D	D	D	D	D	A	A	C
	Fyrquel a60	D	D	D	D	D	B	C	C
	Gallic Acid	D	D	D	D	A	B	A	B
	Gasoline	C	A	A	A	A	C	A	A
	Gelatin	D	A	A	A	A	A	A	A
	Germane (Germanium Tetrahydride)	D	D	D	D	D	D	D	D
	Girling Brake Fluid	D	D	D	D	D	A	C	C
	Glacial Acetic Acid - Acid, Organic	A	B	A	A	D	C	C	D
	Glauber's Salt	D	B	A	A	D	C	A	C
	Gluconic Acid	D	D	D	D	D	A	C	C
	Glucose	A	A	A	A	A	A	A	A
	Glue	D	A	A	A	A	A	A	A
	Glutamic Acid	D	D	D	D	D	A	C	C
	Glutaraldehyde Disinfectant - Aldehyde, Aliphatic, Solution	A	D	D	D	D	D	D	D
	Glutaraldehyde, pure - Aldehyde, Aliphatic	A	D	D	D	D	D	D	D
	Glycerine (Glycerol)	A	A	A	A	D	A	A	A
	Glycerol Dichlorohydrin	D	D	D	D	D	A	C	C
	Glycerol Monochlorohydrin	D	D	D	D	D	A	C	C
	Glycerol Triacetate	D	D	D	D	D	A	C	C
	Glycerophosphoric Acid	D	D	D	D	D	A	C	C
	Glyceryl Phosphate	D	D	D	D	D	A	C	C
	Glycidol	D	D	D	D	D	A	C	C
	Glycol Monoether	D	D	D	D	D	D	D	D
	Glycolic Acid	D	D	D	D	D	A	C	C
	Glycols	D	D	D	D	D	A	A	A
	Glyoxylic Acid	D	D	D	D	D	A	C	C
	Grease Petroleum Base	D	B	A	A	D	D	A	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Green Sulfate Liquor	D	D	D	D	D	A	A	B
	Guanidine Hydrochloride, pure - Amine, Salt	A	D	D	D	D	D	D	D
	Guanidine Isothiocyanate, pure - Amine, Salt	A	D	D	D	D	D	D	D
	Guanidine Thiocyanate, pure - Amine, Salt	A	D	D	D	D	D	D	D
	Gulf Endurance Oils	D	D	D	D	D	C	A	A
	Gulf FR Fluids (Emulsion)	D	D	D	D	D	C	A	A
	Gulf FR G-Fluids	D	D	D	D	D	A	A	A
	Gulf FR P-Fluids	D	D	D	D	D	B	B	C
	Gulf Harmony Oils	D	D	D	D	D	C	A	A
	Gulf High Temperature Grease	D	D	D	D	D	C	A	A
	Gulf Legion Oils	D	D	D	D	D	C	A	A
	Gulf Paramount Oils	D	D	D	D	D	C	A	A
	Gulf Security Oils	D	D	D	D	D	C	A	A
	Gulfcrown Grease	D	D	D	D	D	C	A	A
	Haemo-Sol detergent - Detergent	A	D	D	D	D	D	D	D
	Halothane	D	D	D	D	D	C	A	C
	Halowax Oil	D	D	D	D	D	C	A	C
	Hannifin Lube A	D	D	D	D	D	C	A	A
	Heavy Water	D	D	D	D	D	A	D	A
	HEF-2 (High Energy Fuel)	D	D	D	D	D	C	A	B
	Helium	A	D	D	D	D	A	A	A
	Heptachlor	D	D	D	D	D	C	A	B
	Heptachlorobutene	D	D	D	D	D	C	A	B
	Heptaldehyde (Heptanal)	D	D	D	D	D	C	A	A
	Heptane or n-Heptane	C	A	A	A	A	C	A	A
	Heptanoic Acid	D	D	D	D	D	C	A	A
	Hexachloroacetone	D	D	D	D	D	A	C	C
	Hexachlorobutadiene	D	D	D	D	D	C	A	B
	Hexachlorobutene	D	D	D	D	D	C	A	B
	Hexachloroethane	D	D	D	D	D	C	A	B
	Hexaethyl Tetraphosphate	D	D	D	D	D	D	D	D
	Hexafluoroethane (F-116)	D	D	D	D	D	D	D	D
	Hexafluoroxylene	D	D	D	D	D	D	D	D
	Hexafluoroxylene	D	D	D	D	D	D	D	D
	Hexaldehyde or n-Hexaldehyde	D	D	D	D	D	A	C	C
	Hexamethyldisilazane	D	D	D	D	D	D	D	D
	Hexamethylene (Cyclohexane)	D	D	D	D	D	C	A	A
	Hexamethylene Diammonium Adipate	D	D	D	D	D	C	A	B
	Hexamethylenediamine	D	D	D	D	D	A	C	C
	Hexamethylenetetramine	D	D	D	D	D	A	C	C
	Hexane or n-Hexane	B	A	A	A	D	C	A	A
	Hexanol, pure - Alcohol, Aliphatic	D	A	A	A	D	C	A	A
	Hexene-1 or n-Hexene-1	D	D	D	D	D	C	A	B
	Hexone (Methyl Isobutyl Ketone)	D	D	D	D	D	A	C	C
	Hexyl Acetate	D	D	D	D	D	C	A	A
	Hexyl Alcohol	D	D	D	D	D	C	A	A
	Hexylene Glycol	D	D	D	D	D	A	C	C
	Hexylresorcinol	D	D	D	D	D	C	A	B
	High Viscosity Lubricant, H2	D	D	D	D	D	A	A	A
	High Viscosity Lubricant, U4	D	D	D	D	D	A	A	A
	HiLo MS #1	D	D	D	D	D	A	C	C
	Houghto-Safe 1010 phosphate ester	D	D	D	D	D	A	A	C
	Houghto-Safe 1055 phosphate ester	D	D	D	D	D	A	A	C
	Houghto-Safe 1120 phosphate ester	D	D	D	D	D	B	A	C
	Houghto-Safe 271 (Water & Glycol Base)	D	D	D	D	D	A	B	A
	Houghto-Safe 416 & 500 Series	D	D	D	D	D	A	D	A
	Houghto-Safe 5040 (Water/Oil emulsion)	D	D	D	D	D	C	A	A
	Houghto-Safe 620 Water/Glycol	D	D	D	D	D	A	B	A
	Household Bleach - Base/Caustic, Oxidizer	C	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Hydraulic Oil (Petroleum Base, Industrial)	D	D	D	D	D	C	A	A
	Hydraulic Oils (Synthetic Base)	D	D	D	D	D	C	A	B
	Hydrazine	C	A	A	A	D	A	C	C
	Hydrazine (Anhydrous)	D	D	D	D	D	B	C	C
	Hydrazine Dihydrochloride	D	D	D	D	D	A	C	C
	Hydrazine Hydrate	D	D	D	D	D	A	C	C
	Hydriodic Acid	D	D	D	D	D	C	A	B
	Hydrobietyl Alcohol	D	D	D	D	D	D	D	D
	Hydrobromic Acid	D	C	C	A	A	A	A	C
	Hydrobromic Acid 40%	D	D	D	D	D	A	A	C
	Hydrobromic Acid, 69% - Acid, Organic	A	D	D	D	D	D	D	D
	Hydrocarbons, Saturated	D	D	D	D	D	C	A	A
	Hydrochloric Acid (cold) 37%	A	C	A	A	A	C	A	C
	Hydrochloric Acid (hot) 37%	D	D	D	D	D	C	A	C
	Hydrochloric Acid, >6N - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 10% - Acid, Inorganic	A	C	A	A	D	A	A	C
	Hydrochloric Acid, 1N - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 20% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 25% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 3 Molar to 158°F	D	D	D	D	D	A	A	B
	Hydrochloric Acid, 30% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 35% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 5% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 50% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, 6N - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrochloric Acid, Concentrated Room Temp.	A	D	D	D	A	B	A	B
	Hydrochloric Acid, Concentrated to 158°F	D	D	D	D	D	C	A	C
	Hydrochloric Acid, pure - Acid, Inorganic	A	D	D	D	D	D	D	D
	Hydrocyanic Acid	A	C	A	A	A	A	A	C
	Hydro-Drive MIH-10 (Petroleum Base)	D	D	D	D	D	C	A	A
	Hydro-Drive MIH-50 (Petroleum Base)	D	D	D	D	D	C	A	A
	Hydrofluoric Acid (Anhydrous)	D	C	C	D	D	D	D	D
	Hydrofluoric Acid (conc.) Cold	D	C	C	D	D	D	D	D
	Hydrofluoric Acid (conc.) Hot	D	C	C	D	D	C	C	C
	Hydrofluoric Acid, 10% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 100% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 35% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 38% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 4% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 48% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 50% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 53% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 60% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, 70% - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, concentrated - Acid, Inorganic	B	C	C	D	D	D	D	D
	Hydrofluoric Acid, pure - Acid, Inorganic	A	C	C	D	D	D	D	D
	Hydrofluorosilicic Acid	A	D	D	D	D	A	A	B
	Hydroformic Acid, 100% - Acid, Organic	D	D	D	D	D	D	D	D
	Hydrogen Bromide (Anhydrous)	D	D	D	D	D	D	D	D
	Hydrogen Chloride (Anhydrous)	D	D	D	D	D	D	D	D
	Hydrogen Chloride gas	D	D	D	D	D	A	A	C
	Hydrogen Cyanide	D	C	A	A	D	A	A	C
	Hydrogen Fluoride	D	D	D	D	D	D	D	D
	Hydrogen Fluoride (Anhydrous)	D	D	D	D	D	A	C	C
	Hydrogen Gas, Cold	D	A	A	A	A	A	A	A
	Hydrogen Gas, Hot	D	A	A	A	D	A	A	A
	Hydrogen Iodide (Anhydrous)	D	D	D	D	D	D	D	D
	Hydrogen Peroxide	A	B	C	A	A	D	A	B
	Hydrogen Peroxide 90%	A	D	D	D	A	C	A	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Hydrogen Selenide	D	D	D	D	D	D	D	D
	Hydrogen Sulfide Dry Cold	A	D	D	D	A	A	C	A
	Hydrogen Sulfide Dry Hot	D	D	D	D	A	A	C	C
	Hydrogen Sulfide Wet Cold	A	C	A	A	A	A	C	C
	Hydrogen Sulfide Wet Hot	D	D	D	D	A	A	C	C
	Hydrolube-Water/Ethylene Glycol	D	D	D	D	D	A	A	A
	Hydroxycitronellal	D	D	D	D	D	D	A	D
	Hydroquinol	D	D	D	D	D	C	A	C
	Hydroquinone	A	D	D	D	D	B	B	C
	Hydroxyacetic Acid	D	D	D	D	D	A	C	C
	Hydyne	D	D	D	D	D	A	C	B
	Hyjet	D	D	D	D	D	A	C	C
	Hyjet IV and IVA	D	D	D	D	D	A	C	C
	Hyjet s4	D	D	D	D	D	A	C	C
	Hyjet w	D	D	D	D	D	A	C	C
	Hypochlorous Acid	D	C	C	A	D	B	D	C
	Indole	D	D	D	D	D	D	A	D
	Industron FF44	D	D	D	D	D	C	A	A
	Industron FF48	D	D	D	D	D	C	A	A
	Industron FF53	D	D	D	D	D	C	A	A
	Industron FF80	D	D	D	D	D	C	A	A
	Insulin	D	D	D	D	D	A	C	C
	Iodic Acid	D	D	D	D	D	A	C	C
	Iodine	A	B	C	A	A	C	A	C
	Iodine Crystals - Element, Solid	A	D	D	D	D	D	D	D
	Iodine Pentafluoride	D	D	D	D	D	C	C	C
	Iodoacetic Acid, pure - Acid, Organic, Halogenated	D	D	D	D	D	D	D	D
	Iodoform	D	A	A	A	D	D	D	C
	IPA, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	IPA, 30% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	IPA, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Isoamyl Acetate	D	D	D	D	D	A	C	C
	Isoamyl Butyrate	D	D	D	D	D	A	C	C
	Isoamyl Valerate	D	D	D	D	D	A	C	C
	Isoboreol	D	D	D	D	D	D	A	D
	Isobutane	D	A	A	A	D	C	A	A
	Isobutanol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Iso-Butanol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Isobutanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Iso-Butanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Isobutyl Acetate	D	A	A	A	D	D	C	C
	Isobutyl Alcohol	A	B	A	A	D	D	A	B
	iso-Butyl Alcohol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Isobutyl Alcohol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	iso-Butyl Alcohol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Isobutyl Chloride	D	D	D	D	D	C	A	C
	Isobutyl Ether	D	D	D	D	D	C	C	B
	Isobutyl Methyl Ketone	D	B	A	A	D	D	C	C
	Isobutyl n-Butyrate	D	D	D	D	D	A	A	C
	Isobutyl Phosphate	D	D	D	D	D	A	C	C
	Isobutylene	D	D	D	D	D	D	A	D
	Isobutyraldehyde	D	D	D	D	D	B	C	C
	Isobutyric Acid	D	D	D	D	D	B	C	A
	Isocrotyl Chloride	D	D	D	D	D	D	A	D
	Isodecanol	D	D	D	D	D	C	A	A
	Isododecane	D	D	D	D	D	C	A	A
	Isoeugenol	D	D	D	D	D	C	A	A
	Isooctane	C	D	D	D	A	C	A	A
	Isopentane	D	B	A	A	D	C	A	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Isophorone (Ketone)	D	D	D	D	D	B	C	C
	Isopropanol	A	A	A	A	D	A	A	C
	Isopropyl Acetate	B	A	A	A	D	C	C	C
	Isopropyl Alcohol	A	A	A	A	D	A	A	C
	Isopropyl Benzene, pure - Hydrocarbon, Aromatic	C	D	D	D	D	D	D	D
	Isopropyl Chloride	D	D	D	D	D	C	A	C
	Isopropyl Ether	C	D	D	D	A	C	C	B
	Isopropyl Myristate, pure - Ester, Aliphatic	D	D	D	D	D	D	D	D
	Isopropylacetone	D	D	D	D	D	A	C	C
	Isopropylacetone, pure - Ketone, Aliphatic	D	D	D	D	D	D	D	D
	Isopropylamine	D	A	A	A	D	A	C	C
	Jet Fuel A	C	D	D	D	D	C	A	B
	JP-10	D	A	A	A	D	C	A	C
	JP-3 (MIL-J-5624)	D	A	A	A	D	C	A	A
	JP-4 (MIL-T-5624)	D	A	A	A	D	C	A	A
	JP-5 (MIL-T-5624)	D	A	A	A	D	C	A	A
	JP-6 (MIL-J-25656)	D	A	A	A	D	C	A	A
	JP-8 (MIL-T-83133)	D	A	A	A	D	C	A	A
	JP-9 (MIL-F-81912)	D	A	A	A	D	C	A	D
	JP-9 -11	D	A	A	A	D	C	A	D
	JPX(MIL-F-25604)	D	D	D	D	D	C	C	A
	Kel F Liquids	D	D	D	D	D	A	B	A
	Kerosene (Similar to RP-1 and JP-1)	C	A	A	A	A	C	A	A
	Keystone #87HX-Grease	D	D	D	D	D	C	A	A
	Kodak FTFR Photoresist - Misc., Photoresist	D	D	D	D	D	D	D	D
	Kodak KMER Photoresist - Misc., Photoresist	D	D	D	D	D	D	D	D
	Kodak KTFR Photoresist - Misc., Photoresist	D	D	D	D	D	D	D	D
	Lacquer Solvents	C	D	D	D	D	C	C	C
	Lacquers	D	A	A	A	A	C	C	C
	Lactams-Amino Acids	D	D	D	D	D	B	C	C
	Lactic Acid Cold	A	B	A	A	A	D	A	D
	Lactic Acid Hot	D	D	D	D	A	C	A	C
	Lactones (Cyclic Esters)	D	D	D	D	D	B	C	C
	Lard Animal Fat	D	A	A	A	D	C	A	A
	Lauric Acid	D	D	D	D	D	C	A	A
	Lauryl Alcohol, pure - Alcohol, Aliphatic	D	D	D	D	D	D	D	D
	Lavender Oil	D	D	D	D	D	C	A	B
	LB 135	D	D	D	D	D	A	A	A
	Lead (Molten)	D	D	D	D	D	D	D	D
	Lead Acetate	A	B	A	A	D	A	C	C
	Lead Arsenate	D	D	D	D	D	A	C	C
	Lead Azide	D	D	D	D	D	D	D	D
	Lead Bromide	D	D	D	D	D	A	C	C
	Lead Carbonate	D	D	D	D	D	A	C	C
	Lead Chloride	D	C	A	A	D	D	D	C
	Lead Chromate	D	D	D	D	D	A	C	C
	Lead Dioxide	D	D	D	D	D	A	C	C
	Lead Linoleate	D	D	D	D	D	A	C	C
	Lead Naphthenate	D	D	D	D	D	D	D	D
	Lead Nitrate	D	B	A	A	D	A	C	A
	Lead Oxide	D	D	D	D	D	A	C	C
	Lead Sulfamate	D	D	D	D	D	A	A	B
	Lehigh X1169	D	D	D	D	D	C	A	A
	Lehigh X1170	D	D	D	D	D	C	A	A
	Light Grease	D	D	D	D	D	C	A	A
	Ligroin (Petroleum Ether or Benzene)	D	D	D	D	D	C	A	A
	Lime Bleach	D	D	D	D	D	A	A	A
	Lime Sulfur	D	D	D	D	D	D	A	D
	Lindol, Hydraulic Fluid(Phosphate ester type)	D	D	D	D	D	A	B	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Linoleic Acid	D	D	D	D	D	C	B	B
	Linseed Oil	A	A	A	A	D	C	A	A
	Liquid Oxygen (LOX)	D	D	D	D	D	C	C	C
	Liquid Petroleum Gas (LPG)	D	A	A	A	D	C	A	A
	Liquimoly	D	D	D	D	D	C	A	A
	Lithium Bromide (Brine)	D	D	D	D	D	A	C	C
	Lithium Carbonate	D	D	D	D	D	A	C	C
	Lithium Chloride	D	B	A	A	D	A	C	C
	Lithium Citrate	D	D	D	D	D	A	C	C
	Lithium Hydroxide	D	B	C	A	D	A	C	C
	Lithium Hypochlorite	D	D	D	D	D	A	C	C
	Lithium Nitrate	D	D	D	D	D	A	C	C
	Lithium Nitrite	D	D	D	D	D	A	C	C
	Lithium Perchlorate	D	D	D	D	D	A	C	C
	Lithium Salicylate	D	D	D	D	D	A	C	C
	Lithopone	D	D	D	D	D	A	C	C
	Lubricating Oils (Crude & Refined)	D	A	A	A	D	C	A	B
	Lubricating Oils (Synthetic base)	D	D	D	D	D	D	A	D
	Lubricating Oils, Di-ester	D	D	D	D	D	C	A	B
	Lubricating Oils, petroleum base	D	D	D	D	D	C	A	A
	Lubricating Oils, SAE 10, 20, 30, 40, 50	D	D	D	D	D	C	A	A
	Lye Solutions	D	D	D	D	D	A	B	B
	Magnesium Chloride	A	C	A	A	A	A	A	A
	Magnesium Hydroxide	A	B	A	A	A	A	A	C
	Magnesium Salts	D	D	D	D	D	A	A	A
	Magnesium Sulfitte and Sulfate	A	A	A	A	A	A	A	A
	Magnesium Trisilicate	D	D	D	D	D	D	D	D
	Malathion	D	D	D	D	D	C	A	B
	Maleic Acid	D	B	A	A	D	C	A	C
	Maleic Anhydride	D	A	A	A	D	C	C	C
	Maleic Hydrazide	D	D	D	D	D	A	C	C
	Malic Acid	D	D	D	D	D	B	A	A
	Mandelic Acid	D	D	D	D	D	A	C	C
	Manganese Acetate	D	D	D	D	D	A	C	C
	Manganese Carbonate	D	D	D	D	D	A	C	C
	Manganese Chloride	D	B	A	A	D	D	C	C
	Manganese Dioxide	D	D	D	D	D	A	C	C
	Manganese Gluconate	D	D	D	D	D	A	C	C
	Manganese Hypophosphite	D	D	D	D	D	A	C	C
	Manganese Linoleate	D	D	D	D	D	A	C	C
	Manganese Naphthenate	D	D	D	D	D	D	D	D
	Manganese Phosphate	D	D	D	D	D	A	C	C
	Manganese Salts, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Manganese Sulfate	D	A	A	A	D	A	D	D
	Manganous Chloride	D	D	D	D	D	A	C	C
	Manganous Phosphate	D	D	D	D	D	A	C	C
	Manganous Sulfate	D	D	D	D	D	A	C	C
	Mannitol	D	D	D	D	D	A	C	C
	MCS 312	D	D	D	D	D	C	A	C
	MCS 352	D	D	D	D	D	A	C	C
	MCS 463	D	D	D	D	D	A	C	C
	MDI (Methylene di-p-phenylene isocyanate)	D	D	D	D	D	A	C	C
	Mechanical Oil - Hydrocarbon, Mixture	B	D	D	D	D	D	D	D
	Mercaptan	D	A	A	A	D	D	D	D
	Mercaptoacetic Acid, pure - Acid, Organic	D	D	D	D	D	D	D	D
	Mercaptobenzothiazole (MBT)	D	D	D	D	D	D	A	D
	Mercuric Acetate	D	D	D	D	D	A	C	C
	Mercuric Chloride	A	C	D	D	A	A	A	A
	Mercuric Cyanide	D	D	D	D	A	A	C	C



Customer Tools

CATEGORY	DESCRIPTION									
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N	
A	No known effect									
B	Some effect, evaluate with caution									
C	Moderate to Severe effect, evaluation not recommended									
D	Unknown									
	Mercuric Iodide	D	D	D	D	D	A	C	C	
	Mercuric Nitrate	D	D	D	D	D	A	C	C	
	Mercuric Sulfate	D	D	D	D	D	A	C	C	
	Mercuric Sulfite	D	D	D	D	D	A	C	C	
	Mercurous Nitrate	D	D	D	D	D	A	C	C	
	Mercury	A	A	A	A	A	A	A	A	
	Mercury Chloride	D	D	D	D	D	A	C	C	
	Mercury Fulminate	D	D	D	D	D	A	C	C	
	Mercury Salts	A	D	D	D	D	A	C	C	
	Mercury Vapors	D	D	D	D	D	A	A	A	
	Mesityl Oxide (Ketone)	D	D	D	D	D	B	C	C	
	Mesitylene, pure - Hydrocarbon, Aromatic	C	D	D	D	D	D	D	D	
	Meta-Cresol	D	D	D	D	D	D	A	D	
	Metalddehyde	D	D	D	D	D	A	C	C	
	Meta-Nitroaniline	D	D	D	D	D	A	C	C	
	Meta-Toluidine	D	D	D	D	D	D	A	D	
	Methacrylic Acid	D	D	D	D	D	A	C	C	
	Methallyl Chloride	D	D	D	D	D	D	A	D	
	Methane	D	A	A	A	D	C	A	A	
	Methanol	A	A	A	A	D	A	C	D	
	Methoxychlor	D	D	D	D	D	D	D	D	
	Methoxyethanol (DGMEA)	D	D	D	D	D	A	C	C	
	Methoxyethyl Oleate, pure - Ether, Aliphatic, Ester	A	D	D	D	D	D	D	D	
	Methyl Abietate	D	D	D	D	D	D	A	D	
	Methyl Acetate	B	A	A	A	A	C	C	C	
	Methyl Acetoacetate	D	D	D	D	D	B	C	C	
	Methyl Acetophenone	D	D	D	D	D	D	A	D	
	Methyl Acrylate	D	A	A	A	D	C	C	C	
	Methyl Alcohol	A	D	D	D	A	A	C	C	
	Methyl Amylketone	D	D	D	D	D	A	C	C	
	Methyl Anthranilate	D	D	D	D	D	D	A	D	
	Methyl Benzene, pure - Hydrocarbon, Aromatic	C	D	D	D	D	D	D	D	
	Methyl Benzoate	D	D	D	D	D	C	A	C	
	Methyl Bromide	D	A	A	A	D	C	A	C	
	Methyl Butyl Ketone	D	D	D	D	D	A	C	C	
	Methyl Butyrate Cellosolve	D	D	D	D	D	A	C	C	
	Methyl Butyrate Chloride	D	D	D	D	D	A	C	C	
	Methyl Carbonate	D	D	D	D	D	C	A	C	
	Methyl Cellosolve	B	D	D	D	A	B	C	C	
	Methyl Cellosolve Acetate, pure - Ether, Aliphatic, Polyol	C	D	D	D	D	D	D	D	
	Methyl Cellulose	D	D	D	D	D	B	C	B	
	Methyl Chloride	D	A	A	A	A	C	A	C	
	Methyl Chloroacetate	D	D	D	D	D	A	C	C	
	Methyl Chloroform	D	D	D	D	D	C	A	C	
	Methyl Chloroformate	D	D	D	D	D	C	A	C	
	Methyl Chlorosilanes	D	D	D	D	D	D	D	D	
	Methyl Cyanide (Acetonitrile)	D	D	D	D	D	A	C	C	
	Methyl Cyclohexanone	D	D	D	D	D	C	A	A	
	Methyl Dichloride	D	D	D	D	D	D	A	D	
	Methyl Ether	D	D	D	D	D	C	A	A	
	Methyl Ethyl Ketone (MEK)	A	B	A	A	A	A	C	C	
	Methyl Ethyl Ketone Peroxide	D	D	D	D	D	C	C	C	
	Methyl Ethyl Oleate	D	D	D	D	D	D	A	D	
	Methyl Formate	D	D	D	D	A	B	D	C	
	Methyl Hexyl Ketone (2-Octanone)	D	D	D	D	D	A	C	C	
	Methyl Iodide	D	D	D	D	D	C	A	A	
	Methyl Isobutyl Ketone (MIBK)	B	B	A	A	D	C	C	C	
	Methyl Isocyanate	D	D	D	D	D	A	C	C	
	Methyl Isopropyl Ketone	D	D	D	D	D	B	C	C	



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
Methyl Isovalerate		D	D	D	D	D	D	A	D
Methyl Lactate		D	D	D	D	D	A	C	C
Methyl Mercaptan		D	D	D	D	D	A	D	D
Methyl Methacrylate		D	A	A	A	D	C	C	C
Methyl Oleate		D	D	D	D	D	B	A	C
Methyl Pentadiene		D	D	D	D	D	D	A	D
Methyl Phenylacetate		D	D	D	D	D	D	A	D
Methyl Propyl Ketone, pure - Ketone, Aliphatic		B	D	D	D	D	D	D	D
Methyl Salicylate		D	D	D	D	D	B	D	C
Methyl Tertiary Butyl Ether (MTBE)		D	B	A	A	D	C	C	C
Methyl Valerate		D	D	D	D	D	D	A	D
Methyl-2-Pyrrolidone or n-Methyl-2-Pyrrolidone		D	D	D	D	D	B	D	D
Methylacrylic Acid		D	D	D	D	D	B	C	C
Methylal		D	D	D	D	D	D	D	D
Methylamine		D	D	D	D	D	A	C	C
Methylamyl Acetate		D	D	D	D	D	A	C	C
Methylcyclopentane		D	D	D	D	D	C	A	C
Methylene Bromide		D	D	D	D	D	D	A	D
Methylene Chloride		C	B	A	A	A	C	C	C
Methylene Iodide		D	D	D	D	D	D	A	D
Methylglycerol		D	D	D	D	D	A	C	C
Methylisobutyl Carbinol		D	D	D	D	D	C	A	A
Methylpyrrolidine		D	D	D	D	D	D	A	D
Methylpyrrolidone		D	D	D	D	D	D	A	D
Methylsulfuric Acid		D	D	D	D	D	A	C	C
Methyl-t-Butyl Ether, pure - Ether, Aliphatic		C	D	D	D	D	D	D	D
Metrizamide - Misc.		A	D	D	D	D	D	D	D
MIBK, pure - Ketone, Aliphatic		B	D	D	D	D	D	D	D
MIL-A-6091		D	D	D	D	D	A	A	B
MIL-C-4339		D	D	D	D	D	C	A	A
MIL-C-7024		D	D	D	D	D	C	A	A
MIL-C-8188		D	D	D	D	D	C	B	B
MIL-E-9500		D	D	D	D	D	A	A	A
MIL-F-16884		D	D	D	D	D	C	A	A
MIL-F-17111		D	D	D	D	D	C	A	A
MIL-F-25558 (RJ-1)		D	D	D	D	D	C	A	A
MIL-F-25656		D	D	D	D	D	C	A	A
MIL-F-5566		D	D	D	D	D	A	A	B
MIL-F-81912 (JP-9)		D	D	D	D	D	C	A	C
MIL-F-82522 (RJ-4)		D	D	D	D	D	C	A	B
MIL-G-10924		D	D	D	D	D	C	A	A
MIL-G-15793		D	D	D	D	D	C	A	A
MIL-G-21568		D	D	D	D	D	A	A	A
MIL-G-25013		D	D	D	D	D	A	A	A
MIL-G-25537		D	D	D	D	D	C	A	A
MIL-G-25760		D	D	D	D	D	C	A	B
MIL-G-3278		D	D	D	D	D	C	A	B
MIL-G-3545		D	D	D	D	D	C	A	A
MIL-G-4343		D	D	D	D	D	C	A	B
MIL-G-5572		D	D	D	D	D	C	A	A
MIL-G-7118		D	D	D	D	D	C	A	B
MIL-G-7187		D	D	D	D	D	C	A	A
MIL-G-7421		D	D	D	D	D	C	A	B
MIL-G-7711		D	D	D	D	D	C	A	A
MIL-H-13910		D	D	D	D	D	A	A	A
MIL-H-19457		D	D	D	D	D	B	A	C
MIL-H-22251		D	D	D	D	D	A	D	B
MIL-H-27601		D	D	D	D	D	C	A	A
MIL-H-46170 -15°F to +400°F		D	D	D	D	D	C	A	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
MIL-H-46170	-20°F to +275°F	D	D	D	D	D	C	A	A
MIL-H-46170	-55°F to +275°F	D	D	D	D	D	C	A	A
MIL-H-46170	-65°F to +275°F	D	D	D	D	D	C	A	A
MIL-H-5606	-65°F to +235°F	D	D	D	D	D	C	A	A
MIL-H-5606	-65°F to +275°F	D	D	D	D	D	C	A	A
MIL-H-6083		D	D	D	D	D	C	A	A
MIL-H-7083		D	D	D	D	D	A	B	A
MIL-H-8446 (MLO-8515)		D	D	D	D	D	C	A	B
MIL-J-5161		D	D	D	D	D	C	A	B
Milk		A	D	D	D	A	A	A	A
MIL-L-15016		D	D	D	D	D	C	A	A
MIL-L-15017		D	D	D	D	D	C	A	A
MIL-L-17331		D	D	D	D	D	C	A	A
MIL-L-2104		D	D	D	D	D	C	A	A
MIL-L-21260		D	D	D	D	D	C	A	A
MIL-L-23699		D	D	D	D	D	C	A	B
MIL-L-25681		D	D	D	D	D	A	A	B
MIL-L-3150		D	D	D	D	D	C	A	A
MIL-L-6081		D	D	D	D	D	C	A	A
MIL-L-6082		D	D	D	D	D	C	A	A
MIL-L-6085		D	D	D	D	D	C	A	B
MIL-L-6387		D	D	D	D	D	C	A	B
MIL-L-7808		D	D	D	D	D	C	A	B
MIL-L-7870		D	D	D	D	D	C	A	A
MIL-L-9000		D	D	D	D	D	C	A	A
MIL-L-9236		D	D	D	D	D	C	A	B
MIL-O-3503		D	D	D	D	D	C	A	A
MIL-P-27402		D	D	D	D	D	A	D	B
MIL-R-25576 (RP-1)		D	D	D	D	D	C	A	A
MIL-S-3136, Type I Fuel		D	D	D	D	D	C	A	A
MIL-S-3136, Type II Fuel		D	D	D	D	D	C	A	B
MIL-S-3136, Type III Fuel		D	D	D	D	D	C	A	B
MIL-S-3136, Type IV Oil High Swell		D	D	D	D	D	C	A	A
MIL-S-3136, Type IV Oil Low Swell		D	D	D	D	D	C	A	A
MIL-S-3136, Type V Oil Medium Swell		D	D	D	D	D	C	A	A
MIL-S-81087		D	D	D	D	D	A	A	A
MIL-T-5624, JP-4, JP-5		D	D	D	D	D	C	A	A
MIL-T-83133		D	D	D	D	D	C	A	A
Mineral Oils		A	A	A	A	A	C	A	A
Mineral Spirits - Hydrocarbon, Mixture		C	A	A	A	D	C	A	A
Mixed Acids		D	D	D	D	A	A	C	C
MLO-7277 Hydr.		D	D	D	D	D	C	A	C
MLO-7557		D	D	D	D	D	C	A	C
MLO-8200 Hydr.		D	D	D	D	D	C	A	B
MLO-8515		D	D	D	D	D	C	A	B
Mobil 24dte		D	D	D	D	D	C	A	A
Mobil 254 Lubricant		D	D	D	D	D	D	D	D
Mobil Delvac 1100, 1110, 1120, 1130		D	D	D	D	D	C	A	A
Mobil HF		D	D	D	D	D	C	A	A
Mobil Nivac 20, 30		D	D	D	D	D	A	A	A
Mobil SHC 500 Series		D	D	D	D	D	C	A	C
Mobil SHC 600 Series		D	D	D	D	D	C	A	C
Mobil Therm 600		D	D	D	D	D	C	A	A
Mobil Velocite c		D	D	D	D	D	C	A	A
Mobilgas WA200 ATF		D	D	D	D	D	C	A	A
Mobilgear 600 Series		D	D	D	D	D	C	A	C
Mobilgear SHC ISO Series		D	D	D	D	D	C	A	C
Mobilgrease HP		D	D	D	D	D	C	A	B
Mobilgrease HTS		D	D	D	D	D	C	A	B



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Mobilgrease SM	D	D	D	D	D	C	A	B
	Mobilith AW Series	D	D	D	D	D	C	A	B
	Mobilith SHC Series	D	D	D	D	D	C	A	B
	Mobiljet II Lubricant	D	D	D	D	D	D	D	D
	Mobilmistube Series	D	D	D	D	D	C	A	C
	Mobiloil SAE 20	D	D	D	D	D	C	A	A
	Mobilux	D	D	D	D	D	C	A	A
	Molybdenum Disulfide Grease	D	D	D	D	D	C	A	A
	Molybdenum Oxide	D	D	D	D	D	A	C	C
	Molybdenum Trioxide	D	D	D	D	D	A	C	C
	Molybdic Acid	D	D	D	D	D	A	C	C
	Monobasic Potassium Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Monobasic Sodium Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Monobromobenzene	D	D	D	D	D	C	A	C
	Monobromotoluene	D	D	D	D	D	D	A	D
	Monobutyl Paracresol	D	D	D	D	D	D	D	D
	Monochloroacetic Acid	D	D	D	D	D	A	C	C
	Monochlorobenzene	C	D	D	D	D	C	A	C
	Monochlorobutene	D	D	D	D	D	D	A	D
	Monochloroethane, pure - Hydrocarbon, Aliphatic, Halogenated	C	D	D	D	D	D	D	D
	Monochlorohydrin	D	D	D	D	D	D	D	D
	Monoethanolamine (MEA)	D	A	A	A	D	C	C	C
	Monoethyl Amine	D	D	D	D	D	A	C	C
	Monoisopropylamine	D	D	D	D	D	A	C	C
	Monomethyl Aniline	D	D	D	D	D	A	B	C
	Monomethyl Ether (Dimethyl Ether)	D	D	D	D	D	D	D	D
	Monomethyl Ether (Methyl Ether)	D	D	D	D	D	C	A	A
	Monomethyl Hydrazine	D	D	D	D	D	A	D	B
	Monomethylamine (MMA)	D	D	D	D	D	A	C	C
	Monomethylaniline	D	D	D	D	D	B	B	C
	Mononitrotoluene	D	D	D	D	D	A	C	C
	Mononitrotoluene & Dinitrotoluene(40/60 Mix)	D	D	D	D	D	A	C	C
	Monovinyl Acetylene	D	D	D	D	D	A	A	A
	Mopar Brake Fluid	D	D	D	D	D	A	C	C
	Morpholine	D	D	D	D	D	D	A	D
	Motor Oils	A	D	D	D	D	C	A	A
	MTBE, pure - Ether, Aliphatic	C	D	D	D	D	D	D	D
	Muriatic Acid, pure - Acid, Inorganic	A	C	A	A	D	C	A	C
	Mustard Gas	D	D	D	D	D	D	D	D
	Myristic Acid	D	D	D	D	D	D	A	D
	NALGENE L-900 detergent - Detergent	A	D	D	D	D	D	D	D
	Naphthalene	A	A	A	A	A	C	A	C
	Naphthalene Chloride	D	A	A	A	D	C	A	A
	Naphthalene Sulfonic Acid	D	D	D	D	D	D	A	D
	Naphthalenic Acid	D	D	D	D	D	D	A	D
	Naphthalonic Acid	D	D	D	D	D	D	A	D
	Naphthenic Acid	D	A	A	A	D	C	A	C
	Naphthylamine	D	D	D	D	D	D	D	D
	Naptha	D	A	A	A	A	C	A	C
	Natural Gas	D	D	D	D	A	C	A	A
	n-Butanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	n-Butyl Acetate, pure - Ester, Aliphatic	B	D	D	D	D	D	D	D
	n-Butyl Alcohol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	n-Butyl Phthalate, pure - Ester, Aromatic	C	D	D	D	D	D	D	D
	n-Decane, pure - Hydrocarbon, Aliphatic	C	D	D	D	D	D	D	D
	n-Dodecanol, pure - Alcohol, Aliphatic	D	D	D	D	D	D	D	D
	Neatsfoot Oil	D	D	D	D	D	B	A	A
	Neon	D	D	D	D	D	A	A	A
	Neville Acid	D	D	D	D	D	B	A	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	n-Heptane, pure - Hydrocarbon, Aliphatic	C	D	D	D	D	D	D	D
	n-Hexane, pure - Hydrocarbon, Aliphatic	B	D	D	D	D	D	D	D
	n-Hexanol, pure - Alcohol, Aliphatic	D	D	D	D	D	D	D	D
	Nickel Acetate	D	D	D	D	D	A	C	B
	Nickel Ammonium Sulfate	D	D	D	D	A	A	C	C
	Nickel Chloride	A	B	A	A	A	A	A	A
	Nickel Cyanide	D	D	D	D	D	A	C	C
	Nickel Nitrate	D	D	D	D	D	A	C	C
	Nickel Salts	A	D	D	D	D	A	A	A
	Nickel Sulfate	A	B	D	D	A	A	A	A
	Nicotinamide (Niacinamide)	D	D	D	D	D	D	A	D
	Nicotinamide Hydrochloride	D	D	D	D	D	A	C	C
	Nicotine	D	D	D	D	D	D	A	D
	Nicotine Sulfate	D	D	D	D	D	A	C	C
	Niter Cake	D	D	D	D	D	A	A	A
	Nitric Acid - Red Fuming	D	D	D	D	D	C	B	C
	Nitric Acid - White Fuming	D	D	D	D	D	D	D	D
	Nitric Acid (0 - 50%)	C	A	C	A	A	C	D	C
	Nitric Acid (50 - 100%)	C	D	D	D	A	C	C	C
	Nitric Acid 3 Molar to 158°F	D	D	D	D	D	B	C	C
	Nitric Acid Concentrated Room Temp.	C	D	D	D	D	C	B	D
	Nitric Acid Concentrated to 158°F	C	D	D	D	D	C	C	C
	Nitroaniline	D	D	D	D	D	A	C	C
	Nitrobenzene	C	A	A	A	A	A	C	C
	Nitrobenzoic Acid	D	D	D	D	D	A	C	C
	Nitrocellulose	D	D	D	D	D	A	C	C
	Nitrochlorobenzene	D	D	D	D	D	A	C	C
	Nitrochloroform	D	D	D	D	D	A	C	C
	Nitrodiethylaniline	D	D	D	D	D	A	C	C
	Nitrodiphenyl Ether	D	D	D	D	D	D	D	D
	Nitroethane	D	A	A	A	D	C	C	C
	Nitrofluorobenzene	D	D	D	D	D	A	C	C
	Nitrogen	D	A	A	A	D	A	A	A
	Nitrogen Oxides	D	D	D	D	D	A	C	C
	Nitrogen Tetroxide (N2O4)	D	D	D	D	D	C	C	C
	Nitrogen Trifluoride	D	D	D	D	D	D	D	D
	Nitroglycerine	D	D	D	D	D	A	C	C
	Nitroglycerol	D	D	D	D	D	A	C	C
	Nitroisopropylbenzene	D	D	D	D	D	A	C	C
	Nitromethane	C	A	A	A	D	C	C	C
	Nitrophenol	D	D	D	D	D	A	C	C
	Nitropropane	D	A	A	A	D	B	C	C
	Nitrosyl Chloride	D	D	D	D	D	D	D	D
	Nitrosylsulfuric Acid	D	D	D	D	D	D	D	D
	Nitrothiophene	D	D	D	D	D	A	C	C
	Nitrotoluene	D	D	D	D	D	A	C	C
	Nitrous Acid	D	B	A	A	D	D	C	C
	Nitrous Oxide	D	D	D	D	A	A	A	A
	n-Octane, pure - Hydrocarbon, Aliphatic	A	D	D	D	D	D	D	D
	Nonane	D	D	D	D	D	C	A	A
	Noryl GE Phenolic	D	D	D	D	D	A	D	A
	n-Pentane, pure - Hydrocarbon, Aliphatic	D	D	D	D	D	D	D	D
	n-Pentanol, pure - Alcohol, Aliphatic	D	D	D	D	D	D	D	D
	n-Propane, gas, pure - Hydrocarbon, Aliphatic	C	D	D	D	D	D	D	D
	n-Propane, liquid - Hydrocarbon, Aliphatic	D	D	D	D	D	D	D	D
	n-Propanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	n-Propyl Alcohol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Nycodenz - Misc.	A	D	D	D	D	D	D	D
	Nyvac FR200 Mobil	D	D	D	D	D	A	A	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Octachloro Toluene	D	D	D	D	D	C	A	C
	Octadecane	D	D	D	D	D	C	A	A
	Octanal (n-Octanaldehyde)	D	D	D	D	D	C	A	A
	Octane or n-Octane	D	D	D	D	D	C	A	A
	Octyl Acetate	D	D	D	D	D	A	C	C
	Octyl Alcohol	D	D	D	D	D	C	A	B
	Octyl Chloride	D	D	D	D	D	C	A	A
	Octyl Phthalate	D	D	D	D	D	D	A	D
	o-Dichlorobenzene, pure - Hydrocarbon, Aromatic, Halogenated	C	D	D	D	D	D	D	D
	Oil of Wintergreen, pure - Ester, Aromatic	D	D	D	D	D	D	D	D
	Oil, Cedarwood, pure - Misc.	C	D	D	D	D	D	D	D
	Oil, Cinnamon, pure - Misc.	C	D	D	D	D	D	D	D
	Oil, Cottonseed, pure - Misc.	A	D	D	D	D	D	D	D
	Oil, Linseed, pure - Misc.	A	D	D	D	D	D	D	D
	Oil, Mineral - Hydrocarbon, Mixture	A	D	D	D	D	D	D	D
	Oil, Paraffin, pure - Hydrocarbon, Mixture	B	D	D	D	D	D	D	D
	Oil, Sesame, pure - Misc.	D	D	D	D	D	D	D	D
	Oil, Wintergreen, pure - Ester, Aromatic	D	D	D	D	D	D	D	D
	Olefins	D	D	D	D	D	D	A	D
	Oleic Acid	A	B	A	A	A	C	C	C
	Oleum (Fuming Sulfuric Acid)	C	B	C	A	D	C	A	C
	Oleum Spirits	D	D	D	D	A	C	A	B
	Oleyl Alcohol	D	D	D	D	D	D	A	D
	Olive Oil	D	A	A	A	D	C	A	A
	Orange Oil, pure - Misc.	B	D	D	D	D	D	D	D
	Oronite 8200	D	D	D	D	D	C	A	B
	Oronite 8515	D	D	D	D	D	C	A	B
	Ortho-Chloro Ethyl Benzene	D	D	D	D	D	C	A	C
	Ortho-Chloroaniline	D	D	D	D	D	A	C	C
	Ortho-Chlorophenol	D	D	D	D	D	A	C	C
	Ortho-Cresol	D	D	D	D	D	A	C	C
	Ortho-Dichlorobenzene	D	D	D	D	D	C	A	C
	Ortho-Nitrotoluene	D	D	D	D	D	A	C	C
	Orthophos Acid	D	D	D	D	D	D	D	D
	OS 45 Type III (OS45)	D	D	D	D	D	C	A	B
	OS 45 Type IV (OS45-1)	D	D	D	D	D	C	A	B
	OS 70	D	D	D	D	D	C	A	B
	Oxalic Acid	A	C	A	A	A	A	A	C
	Oxygen, 200-300°F (Evaluate for specific apps)	D	D	D	D	A	C	B	C
	Oxygen, 300-400°F (Evaluate for specific apps)	D	D	D	D	A	C	B	C
	Oxygen, Cold (Evaluate for specific applications)	D	D	D	D	A	A	A	B
	Oxygen, gas, pure - Element, Gas	C	A	A	A	D	C	C	C
	Oxygen, Liquid	D	D	D	D	D	C	C	C
	Ozonated Deionized Water	D	D	D	D	D	A	C	C
	Ozone	C	A	A	A	A	D	A	C
	Ozone, 10ppm in Water - Oxidizer, Inorganic, Solution	C	D	D	D	D	D	D	D
	Paint Thinner, Duco	D	D	D	D	D	C	B	C
	Palmitic Acid	D	A	A	A	A	C	A	A
	Para-Aminobenzoic Acid	D	D	D	D	D	A	C	C
	Para-Aminosalicylic Acid	D	D	D	D	D	A	C	C
	Para-Bromobenzylphenyl Ether	D	D	D	D	D	D	D	D
	Para-Chlorophenol	D	D	D	D	D	A	C	C
	Paracymene	D	A	A	A	D	C	A	C
	Para-Dichlorobenzene	D	D	D	D	D	C	A	C
	Paraffins	B	A	A	A	D	C	A	A
	Para-Formaldehyde	D	A	A	A	D	D	C	C
	Paraldehyde	D	A	A	A	D	D	C	C
	Par-al-Ketone	D	D	D	D	D	C	C	C
	Para-Nitroaniline	D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Para-Nitrobenzoic Acid	D	D	D	D	D	A	C	C
	Para-Nitrophenol	D	D	D	D	D	A	C	C
	Parathion	D	D	D	D	D	D	A	D
	Para-Toluene Sulfonic Acid	D	D	D	D	D	A	C	C
	Parker O Lube	D	D	D	D	D	C	A	A
	p-Chloroacetophenone, pure - Ketone, Aromatic, Halogenated	A	D	D	D	D	D	D	D
	p-Dichlorobenzene, pure - Hydrocarbon, Aromatic, Halogenated	B	D	D	D	D	D	D	D
	Peanut Oil	A	A	A	A	D	C	A	A
	Peanut oil, pure - Misc.	A	A	A	A	D	C	A	A
	Pectin (Liquor)	D	A	A	A	D	C	A	A
	Pelagonic Acid	D	D	D	D	D	D	D	D
	Penicillin (Liquid)	D	A	A	A	D	C	A	D
	Pentachloroethane	D	D	D	D	D	D	A	D
	Pentachlorophenol	D	D	D	D	D	A	C	C
	Pentaerythritol	D	D	D	D	D	A	C	C
	Pentaerythritol Tetranitrate	D	D	D	D	D	A	C	C
	Pentafluoroethane (F-125)	D	D	D	D	D	D	D	D
	Pentane or n-Pentane	D	B	A	A	D	C	A	A
	Pentane, 2 Methyl	D	D	D	D	D	C	A	A
	Pentane, 2-4 dimethyl	D	D	D	D	D	C	A	A
	Pentane, 3-Methyl	D	D	D	D	D	C	A	A
	Pentanol, pure - Alcohol, Aliphatic	D	D	D	D	D	D	D	D
	Pentoxone	D	D	D	D	D	D	D	D
	Pentyl Pentanoate	D	D	D	D	D	C	A	A
	Peracetic Acid	A	D	D	D	D	A	C	C
	Perchloric Acid - 2N	D	D	D	D	D	A	A	C
	Perchloric Acid, 10% - Acid, Inorganic, Oxidizer	D	D	D	D	D	D	D	D
	Perchloric Acid, 25% - Acid, Inorganic, Oxidizer	D	D	D	D	D	D	D	D
	Perchloric Acid, 60% - Acid, Inorganic, Oxidizer	B	D	D	D	D	D	D	D
	Perchloric Acid, 70% - Acid, Inorganic, Oxidizer	B	D	D	D	D	D	D	D
	Perchloric Acid, concentrated - Acid, Inorganic, Oxidizer	B	D	D	D	D	D	D	D
	Perchloric Acid, pure - Acid, Inorganic, Oxidizer	B	D	D	D	D	D	D	D
	Perchloroethylene	C	B	A	A	A	C	A	C
	Percoll - Misc.	A	D	D	D	D	D	D	D
	Perfluoropropane	D	D	D	D	D	D	D	D
	Perfluorotriethylamine	D	D	D	D	D	D	D	D
	Permanganic Acid	D	D	D	D	D	D	D	D
	Persulfuric Acid (Caro's Acid)	D	B	A	A	D	D	D	D
	Petrol - Hydrocarbon, Mixture	C	D	D	D	D	D	D	D
	Petrolatum	D	D	D	D	D	C	A	A
	Petrolatum Ether	D	D	D	D	D	C	A	A
	Petroleum Oil, Above 250°F	C	A	A	A	A	C	A	D
	Petroleum Oil, Below 250°F	C	D	D	D	A	C	A	A
	Petroleum Oil, Crude	C	D	D	D	A	C	A	A
	Phenol	D	B	A	A	A	C	A	C
	Phenol, 10% - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenol, 10% Aqueous - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenol, 100% - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenol, 5% - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenol, 50% - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenol, 70%/30% H2O	D	D	D	D	D	C	A	C
	Phenol, 85%/15% H2O	D	D	D	D	D	C	A	C
	Phenol, 92% - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenol, Crystals, pure - Alcohol, Aromatic	B	D	D	D	D	D	D	D
	Phenol, liquid - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenol, pure - Alcohol, Aromatic	C	D	D	D	D	D	D	D
	Phenolic Sulfonate	D	D	D	D	D	A	C	C
	Phenolsulfonic Acid	D	D	D	D	D	A	C	C
	Phenylacetamide	D	D	D	D	D	D	A	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Phenylacetate	D	D	D	D	D	A	C	C
	Phenylacetic Acid	D	B	A	A	D	A	C	C
	Phenylbenzene	D	D	D	D	D	C	A	C
	Phenylene Diamine	D	D	D	D	D	D	D	D
	Phenylethanol, pure - Alcohol, Aromatic	D	D	D	D	D	D	D	D
	Phenylethyl Alcohol	D	D	D	D	D	D	A	D
	Phenylethyl Ether	D	D	D	D	D	C	C	C
	Phenylethyl Malonic Ester	D	D	D	D	D	D	A	D
	Phenylglycerine	D	D	D	D	D	A	C	C
	Phenylhydrazine	D	D	D	D	D	B	A	C
	Phenylhydrazine Hydrochloride	D	D	D	D	D	A	C	C
	Phenylmercuric Acetate	D	D	D	D	D	A	C	C
	Phorone	D	D	D	D	D	C	C	C
	Phosgene	D	C	A	A	D	C	C	C
	Phosphine	D	D	D	D	D	D	D	D
	Phosphoric Acid 3 Molar to 158°F	D	D	D	D	A	A	A	A
	Phosphoric Acid Concentrated Room Temp	A	D	D	D	A	A	A	B
	Phosphoric Acid Concentrated to 158°F	D	D	D	D	A	A	A	C
	Phosphoric Acid, 10% - Acid, Inorganic	A	A	A	A	D	A	A	C
	Phosphoric Acid, 20%	D	A	A	A	A	A	A	C
	Phosphoric Acid, 25% - Acid, Inorganic	A	A	A	A	D	A	A	C
	Phosphoric Acid, 30% - Acid, Inorganic	A	A	A	A	D	A	A	C
	Phosphoric Acid, 45%	D	A	A	A	A	A	A	C
	Phosphoric Acid, 5% - Acid, Inorganic	A	A	A	A	D	A	A	C
	Phosphoric Acid, 50% - Acid, Inorganic	A	A	A	A	D	A	A	C
	Phosphoric Acid, 85% - Acid, Inorganic	A	A	A	A	D	A	A	C
	Phosphoric Acid, 88% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Phosphoric Acid, 95% - Acid, Inorganic	A	D	D	D	D	D	D	D
	Phosphorus (Molten)	D	D	D	D	D	D	D	D
	Phosphorus Oxychloride	D	C	A	A	D	C	C	C
	Phosphorus Trichloride	D	A	A	A	D	A	A	C
	Phosphorus Trichloride Acid	D	D	D	D	D	A	A	C
	Photographic Hypo - Salt, Inorganic, Reducer	A	D	D	D	D	D	D	D
	Photoresists - Misc., Photoreist	D	D	D	D	D	D	D	D
	Phthalic Acid	D	A	A	A	D	D	C	C
	Phthalic Anhydride	D	A	A	A	D	D	C	C
	Pickling Solution	D	D	D	D	D	C	B	C
	Picric Acid (aq)	C	B	A	A	A	D	A	D
	Picric Acid Molten	D	D	D	D	D	B	A	B
	Pine Oil	A	D	D	D	D	C	A	A
	Pine Tar	D	D	D	D	D	C	A	A
	Pinene	D	D	D	D	D	C	A	B
	Piperazine	D	D	D	D	D	D	A	D
	Piperidine	D	D	D	D	D	C	A	C
	Piranha (H2SO4:H2O2)(70:30)	D	D	D	D	D	D	D	D
	Plating Solution(Co,Cu,Au,In,Fe,Pb,Ni,Ag,Sn,Zn)	D	D	D	D	D	A	A	A
	Plating Solutions Chrome	D	C	C	A	D	B	A	C
	Plating Solutions Others	D	D	D	D	D	A	A	A
	Pneumatic Service	D	D	D	D	D	A	A	A
	Polyethylene Glycol	D	A	A	A	D	A	D	C
	Polyglycerol	D	D	D	D	D	A	C	C
	Polyglycol	D	D	D	D	D	A	C	C
	Polyvinyl Acetate Emulsion	D	D	D	D	D	A	D	D
	Potassium (Molten)	D	D	D	D	D	D	D	D
	Potassium Acetate	A	D	D	D	D	A	C	B
	Potassium Acid Sulfate	D	D	D	D	D	A	C	C
	Potassium Alum	D	D	D	D	D	A	C	C
	Potassium Aluminum Sulfate	D	D	D	D	D	A	C	C
	Potassium Antimonate	D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Potassium Bicarbonate	D	B	A	A	D	D	D	D
	Potassium Bichromate	D	D	D	D	D	A	C	C
	Potassium Bifluoride	D	D	D	D	D	A	C	C
	Potassium Bisulfate	D	D	D	D	D	A	C	C
	Potassium Bisulfite	D	D	D	D	D	A	C	C
	Potassium Bitartrate	D	D	D	D	D	A	C	C
	Potassium Bromide	A	D	D	D	D	A	C	C
	Potassium Carbonate	A	B	A	A	D	D	D	D
	Potassium Chlorate	A	D	D	D	D	A	C	C
	Potassium Chloride	A	B	D	D	A	A	A	A
	Potassium Chromates	D	D	D	D	D	A	C	C
	Potassium Citrate	D	D	D	D	D	A	C	C
	Potassium Cupro Cyanide	D	D	D	D	D	A	A	A
	Potassium Cyanate	D	D	D	D	D	A	C	C
	Potassium Cyanide	A	B	A	A	A	A	A	A
	Potassium Dichromate	D	D	D	D	D	A	A	A
	Potassium Dihydrogen Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Potassium Diphosphate	D	D	D	D	D	A	C	C
	Potassium Ferricyanide	D	D	D	D	D	A	C	C
	Potassium Fluoride	D	D	D	D	D	A	C	C
	Potassium Glucocyanate	D	D	D	D	D	A	C	C
	Potassium Hydroxide 50%	A	C	A	A	A	A	C	C
	Potassium Hydroxide, 1% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Potassium Hydroxide, 10% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Potassium Hydroxide, 15% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Potassium Hydroxide, 1N - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Potassium Hydroxide, 30% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Potassium Hydroxide, 32% - Base/Caustic, Inorganic	A	B	A	A	D	A	C	C
	Potassium Hydroxide, 3N - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Potassium Hydroxide, 45% - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Potassium Hydroxide, 5% - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Potassium Hydroxide, 6N - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Potassium Hydroxide, concentrated - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Potassium Hydroxide, pure - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Potassium Hypochlorite	D	D	D	D	D	A	C	C
	Potassium Iodate	D	D	D	D	D	A	C	C
	Potassium Iodide	A	D	D	D	D	A	C	C
	Potassium Metabisulfate	D	D	D	D	D	A	C	C
	Potassium Metachromate	D	D	D	D	D	A	C	C
	Potassium Metasilicate	D	D	D	D	D	D	D	D
	Potassium Monochromate	D	D	D	D	D	A	C	C
	Potassium Nitrate	D	B	A	A	D	A	A	A
	Potassium Nitrite	D	D	D	D	D	A	C	C
	Potassium Oxalate	D	D	D	D	D	A	C	C
	Potassium Perchlorate	D	D	D	D	D	A	C	C
	Potassium Perfluoro Acetate	D	D	D	D	D	D	D	D
	Potassium Permanganate	D	B	A	A	D	A	C	C
	Potassium Permanganate, pure - Salt, Inorganic, Oxidizer	A	D	D	D	D	D	D	D
	Potassium Peroxide	D	D	D	D	D	D	D	D
	Potassium Persulfate	D	D	D	D	D	A	C	C
	Potassium Phosphate (Acid)	D	B	A	A	A	A	D	D
	Potassium Phosphate (Alkaline)	D	B	A	A	A	A	D	D
	Potassium Phosphate (Di/Tri Basic)	A	D	D	D	A	A	C	C
	Potassium Phosphate Monobasic, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Potassium Pyrosulfate	D	D	D	D	D	A	C	C
	Potassium Salts	D	D	D	D	D	A	A	A
	Potassium Silicate	D	B	A	A	D	A	A	A
	Potassium Sodium Tartrate	D	D	D	D	D	A	C	C
	Potassium Stannate	D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
Potassium Stearate		D	D	D	D	D	A	C	C
Potassium Sulfate		A	A	A	A	A	A	A	A
Potassium Sulfide		D	D	D	D	A	A	C	C
Potassium Sulfite		D	D	D	D	A	A	A	A
Potassium Tartrate		D	D	D	D	D	A	C	C
Potassium Thiocyanate		D	D	D	D	D	A	C	C
Potassium Thiosulfate		D	D	D	D	D	A	C	C
Potassium Triphosphate		D	D	D	D	D	A	C	C
Prestone Antifreeze		D	D	D	D	D	A	A	A
PRL-High Temp. Hydr. Oil		D	D	D	D	D	C	A	B
Producer Gas		D	D	D	D	D	C	A	A
Propane		C	A	A	A	A	C	A	A
Propane, liquid - Hydrocarbon, Aliphatic		D	A	A	A	D	C	A	A
Propanol, pure - Alcohol, Aliphatic		A	D	D	D	D	D	D	D
Propionaldehyde		D	A	A	A	D	A	C	C
Propionic Acid		A	B	A	A	D	A	C	C
Propionitrile		D	D	D	D	D	C	A	A
Propyl Acetate		B	A	A	A	D	C	C	C
Propyl Acetone or n-Propyl Acetone		D	D	D	D	D	A	C	C
Propyl Alcohol		A	A	A	A	A	A	A	A
Propyl Nitrate		A	D	D	D	D	B	C	C
Propyl Propionate		D	D	D	D	D	A	C	C
Propylamine		D	D	D	D	D	A	C	C
Propylbenzene		D	D	D	D	D	D	A	D
Propylene		D	A	A	A	D	C	A	C
Propylene Chloride		D	D	D	D	D	D	A	D
Propylene Chlorohydrin		D	D	D	D	D	D	A	D
Propylene Dichloride		D	D	D	D	D	D	A	D
Propylene Glycol		A	A	A	A	D	A	D	D
Propylene Glycol Acetate, pure - Ester, Aliphatic, Polyol		D	D	D	D	D	D	D	D
Propylene Imine		D	D	D	D	D	D	A	D
Propylene Oxide		A	A	A	A	D	C	C	C
Prussic Acid, Hydrogen, pure - Acid, Inorganic		A	D	D	D	D	D	D	D
Pseudocumene, pure - Hydrocarbon, Aromatic		C	D	D	D	D	D	D	D
Pydraul 90e		D	D	D	D	D	A	A	C
Pydraul, 10E		D	D	D	D	D	A	C	C
Pydraul, 115E		D	D	D	D	D	A	A	C
Pydraul, 230C, 312C, 540C, A200		D	D	D	D	D	C	A	C
Pydraul, 29ELT 30E, 50E, 65E		D	D	D	D	D	A	A	C
Pyranol Transformer Oil		D	D	D	D	D	C	A	A
Pyridine		A	A	A	A	D	C	D	C
Pyridine Oil		D	D	D	D	D	B	C	C
Pyridine Sulfate		D	D	D	D	D	A	C	C
Pyridine Sulfonic Acid		D	D	D	D	D	A	C	C
Pyridine, 5% - Amine, Heterocyclic		A	D	D	D	D	D	D	D
Pyridine, 50% - Amine, Heterocyclic		A	D	D	D	D	D	D	D
Pyrogallol (Pyrogallic Acid)		D	D	D	D	D	C	A	B
Pyrogard 42, 43, 55		D	D	D	D	D	A	A	C
Pyrogard 53, Mobil Phosphate Ester		D	D	D	D	D	A	A	C
Pyrogard D, Mobil Water-in-Oil Emulsion		D	D	D	D	D	C	C	A
Pyroligneous Acid		D	D	D	D	D	B	C	C
Pyrolube		D	D	D	D	D	B	A	C
Pyrosulfuric Acid		D	D	D	D	D	A	C	C
Pyrosulfuryl Chloride		D	D	D	D	D	C	A	B
Pyrrole		D	D	D	D	D	C	C	C
Pyruvic Acid		D	D	D	D	D	A	C	C
Quinidine		D	D	D	D	D	C	A	B
Quinine		D	D	D	D	D	C	A	B
Quinine Bisulfate		D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Quinine Hydrochloride	D	D	D	D	D	A	C	C
	Quinine Sulfate	D	D	D	D	D	A	C	C
	Quinine Tartrate	D	D	D	D	D	A	C	C
	Quinizarin	D	D	D	D	D	C	A	B
	Quinoline	D	D	D	D	D	C	A	B
	Quinone	D	D	D	D	D	C	A	B
	Radiation (GAMMA, 1.0 E+07 RADS)	D	D	D	D	D	B	C	C
	Raffinate	D	D	D	D	D	C	A	B
	Rapeseed Oil	D	D	D	D	D	A	A	B
	Red Line 100 Oil	D	D	D	D	D	C	A	A
	Red Oil (MIL-H-5606)	D	D	D	D	D	C	A	A
	Resorcinol	A	D	D	D	D	A	C	C
	Resorcinol, pure - Alcohol, Aromatic, Polyol	A	D	D	D	D	D	D	D
	Resorcinol, saturated - Alcohol, Aromatic, Polyol	A	D	D	D	D	D	D	D
	Rhodium	D	D	D	D	D	D	D	D
	Riboflavin	D	D	D	D	D	C	A	B
	Ricinoleic Acid	D	D	D	D	D	C	A	B
	RJ-1 (MIL-F-25558)	D	D	D	D	D	C	A	A
	RJ-4 (MIL-F-82522)	D	D	D	D	D	C	A	B
	Rosin	D	D	D	D	D	C	A	B
	RP-1 (MIL-R-25576)	D	D	D	D	D	C	A	A
	Rubidium Bromide, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Rubidium Chloride, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Saccharin Solution	D	D	D	D	D	A	C	C
	Sal Ammoniac	A	D	D	D	D	A	A	A
	Saicylaldehyde, pure - Ester, Aromatic	A	D	D	D	D	D	D	D
	Salicylic Acid	A	B	A	A	D	A	A	C
	Santo Safe 300	D	D	D	D	D	C	A	C
	SDS, pure - Detergent	A	D	D	D	D	D	D	D
	Sea (Salt) Water	A	B	A	A	A	A	A	A
	Sebacic Acid	D	D	D	D	D	A	C	C
	sec-Butanol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	sec-Butanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	sec-Butyl Alcohol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	sec-Butyl Alcohol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Selenic Acid	D	D	D	D	D	A	C	C
	Selenous Acid	D	D	D	D	D	A	C	C
	Sera - Misc.	A	D	D	D	D	D	D	D
	Sesame Oil, pure - Misc.	D	D	D	D	D	D	D	D
	Sewage	D	A	A	A	D	A	A	A
	SF 1154 GE Silicone Fluid	D	D	D	D	D	A	A	B
	SF1147 GE Silicone Fluid	D	D	D	D	D	C	A	B
	SF96 GE Silicone Fluid	D	D	D	D	D	A	A	B
	Shell 3XF Mine Fluid (Fire resist hydr.)	D	D	D	D	D	C	A	A
	Shell Alvania Grease #2	D	D	D	D	D	C	A	A
	Shell Carnea 19 and 29	D	D	D	D	D	C	A	A
	Shell Diala	D	D	D	D	D	C	A	A
	Shell Irus 905	D	D	D	D	D	C	A	A
	Shell Lo Hydrax 27 and 29	D	D	D	D	D	C	A	A
	Shell Macome 72	D	D	D	D	D	C	A	A
	Shell Tellus #32 Pet. Base	D	D	D	D	D	C	A	A
	Shell Tellus #68	D	D	D	D	D	C	A	A
	Shell Tellus 27 (Petroleum Base)	D	D	D	D	D	C	A	A
	Shell Tellus 33	D	D	D	D	D	C	A	A
	Shell UMF (5% Aromatic)	D	D	D	D	D	C	A	A
	Shellac	D	D	D	D	A	A	C	C
	Shipley AZ-111 Photoresist - Misc., Photoresist	D	D	D	D	D	D	D	D
	Shipley AZ-1350 Photoresist - Misc., Photoresist	D	D	D	D	D	D	D	D
	Shipley AZ-340 Photoresist - Misc., Photoresist	D	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Silane	D	D	D	D	D	D	D	D
	Silica Gel, pure - Acid, Inorganic	D	D	D	D	D	D	D	D
	Silicate Esters	D	D	D	D	D	C	A	B
	Silicic Acid, pure - Acid, Inorganic	D	D	D	D	D	D	D	D
	Silicon Fluoride	D	D	D	D	D	D	D	D
	Silicon Tetrachloride	D	D	D	D	D	D	D	D
	Silicon Tetrafluoride	D	D	D	D	D	D	D	D
	Silicone Greases	D	D	D	D	D	A	A	A
	Silicone Oils	A	A	A	A	D	A	A	A
	Silver Acetate, pure - Salt, Organic	A	D	D	D	D	D	D	D
	Silver Bromide	D	D	D	D	D	A	C	C
	Silver Chloride	D	C	A	A	D	A	D	D
	Silver Cyanide	A	D	D	D	D	A	C	C
	Silver Nitrate	A	A	A	A	D	A	A	C
	Silver Sulfate	D	D	D	D	D	A	C	C
	Sinclair Opaline CX-EP Lube	D	D	D	D	D	C	A	A
	Skelly, Solvent B, C, E	D	D	D	D	D	C	A	A
	Skydrol 500 B4	D	D	D	D	D	A	C	C
	Skydrol 7000	D	D	D	D	D	A	B	C
	Skydrol LD-4	A	D	D	D	D	A	C	C
	Soap Solutions	D	A	A	A	A	A	A	A
	Socony Mobile Type A	D	D	D	D	D	C	A	A
	Socony Vacuum AMV AC781 (grease)	D	D	D	D	D	C	A	A
	Socony Vacuum PD959B	D	D	D	D	D	C	A	A
	Soda Ash	D	A	A	A	D	A	A	A
	Sodium (Molten)	D	D	D	D	D	D	D	D
	Sodium Acetate	A	B	A	A	A	A	C	C
	Sodium Acid Bisulfate	D	D	D	D	A	A	C	C
	Sodium Acid Fluoride	D	D	D	D	D	A	C	C
	Sodium Acid Sulfate	D	D	D	D	D	A	C	C
	Sodium Aluminate	D	D	D	D	D	A	C	C
	Sodium Aluminate Sulfate	D	D	D	D	D	A	C	C
	Sodium Anthraquinone Disulfate	D	D	D	D	D	A	C	C
	Sodium Antimonate	D	D	D	D	D	A	C	C
	Sodium Arsenate	D	D	D	D	D	A	C	C
	Sodium Arsenite	D	D	D	D	D	A	C	C
	Sodium Benzoate	D	D	D	D	D	A	C	C
	Sodium Bicarbonate (Baking Soda)	A	A	A	A	D	A	A	A
	Sodium Bichromate	D	D	D	D	D	A	C	C
	Sodium Bifluoride	D	D	D	D	D	A	C	C
	Sodium Bisulfate or Bisulfite	A	C	A	A	D	A	A	A
	Sodium Bisulfide	D	D	D	D	D	A	C	C
	Sodium Bitartrate	D	D	D	D	D	A	C	C
	Sodium Borate	A	A	A	A	D	A	A	A
	Sodium Bromate	D	D	D	D	D	A	C	C
	Sodium Bromide	A	B	A	A	D	A	C	C
	Sodium Carbonate (Soda Ash)	A	A	A	A	A	A	A	A
	Sodium Carbonate, 2% - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Sodium Chlorate	A	B	A	A	A	A	D	C
	Sodium Chloride	A	B	A	A	A	A	A	A
	Sodium Chlorite	D	D	D	D	D	A	C	C
	Sodium Chloroacetate	D	D	D	D	D	A	C	C
	Sodium Chromate	D	A	C	A	D	D	C	D
	Sodium Citrate	D	D	D	D	D	A	C	C
	Sodium Cyanamide	D	D	D	D	D	A	C	C
	Sodium Cyanate	D	D	D	D	D	A	C	C
	Sodium Cyanide	A	C	A	A	A	A	C	A
	Sodium Diacetate	D	D	D	D	D	A	C	C
	Sodium Dichromate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Sodium Dihydrogen Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Sodium Diphenyl Sulfonate	D	D	D	D	D	A	C	C
	Sodium Diphosphate	D	D	D	D	D	A	C	C
	Sodium Disilicate	D	D	D	D	D	A	C	C
	Sodium Dodecyl Sulfate, pure - Detergent	A	D	D	D	D	D	D	D
	Sodium Ethylate	D	D	D	D	D	A	C	C
	Sodium Ferricyanide	D	B	A	A	D	A	D	C
	Sodium Ferrocyanide	D	D	D	D	D	A	C	C
	Sodium Fluoride	D	D	D	D	D	A	C	C
	Sodium Fluorosilicate	D	D	D	D	D	A	C	C
	Sodium Glutamate	D	D	D	D	D	A	C	C
	Sodium Hydride	D	D	D	D	D	D	D	D
	Sodium Hydrogen Sulfate	D	D	D	D	D	A	C	C
	Sodium Hydrosulfide	D	A	A	A	D	A	C	C
	Sodium Hydrosulfite	D	D	D	D	D	A	C	C
	Sodium Hydroxide, <1% - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Sodium Hydroxide, 1% - Base/Caustic, Inorganic	A	A	A	A	D	A	C	C
	Sodium Hydroxide, 10% - Base/Caustic, Inorganic	A	A	A	A	D	A	C	C
	Sodium Hydroxide, 1N - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Sodium Hydroxide, 3 Molar	A	D	D	D	A	A	B	B
	Sodium Hydroxide, 32% - Base/Caustic, Inorganic	A	C	A	A	D	A	C	C
	Sodium Hydroxide, 5% - Base/Caustic, Inorganic	A	A	A	A	D	A	C	C
	Sodium Hydroxide, 50% - Base/Caustic, Inorganic	A	C	A	A	D	A	C	C
	Sodium Hydroxide, 52% - Base/Caustic, Inorganic	A	C	A	A	D	A	C	C
	Sodium Hydroxide, 6N - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Sodium Hydroxide, concentrated - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Sodium Hydroxide, pure - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Sodium Hypochlorite	C	C	C	A	A	A	A	C
	Sodium Hypophosphate	D	D	D	D	D	A	C	C
	Sodium Hypophosphite	D	D	D	D	D	A	C	C
	Sodium Hyposulfite	D	D	D	D	D	A	C	C
	Sodium Iodide	A	D	D	D	D	A	C	C
	Sodium Lactate	D	D	D	D	D	A	C	C
	Sodium Lauryl Sulfate, pure - Detergent	A	D	D	D	D	D	D	D
	Sodium Metaborate, pure - Salt, Inorganic	D	D	D	D	D	D	D	D
	Sodium Metaphosphate	D	D	D	D	A	A	A	A
	Sodium Metasilicate	D	A	A	A	A	A	D	D
	Sodium Methylate	D	D	D	D	D	A	C	C
	Sodium Monophosphate	D	D	D	D	D	A	C	C
	Sodium Nitrate	A	A	A	A	A	A	C	C
	Sodium Oleate	D	D	D	D	D	A	C	C
	Sodium Orthosilicate	D	D	D	D	D	A	C	C
	Sodium Oxalate	D	D	D	D	D	A	C	C
	Sodium Perborate	A	D	D	D	A	A	A	B
	Sodium Percarbonate	D	D	D	D	D	A	C	C
	Sodium Perchlorate	D	B	A	A	D	A	C	C
	Sodium Peroxide	D	D	D	D	A	A	A	B
	Sodium Persulfate	D	D	D	D	D	A	C	C
	Sodium Phenolate	D	D	D	D	D	A	C	C
	Sodium Phenoxide	D	D	D	D	D	A	C	C
	Sodium Phosphate (Dibasic)	A	A	A	A	A	A	A	A
	Sodium Phosphate (Mono)	A	A	A	A	A	A	A	A
	Sodium Phosphate (Tribasic)	D	A	A	A	A	A	A	A
	Sodium Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Sodium Plumbite	D	D	D	D	D	A	C	C
	Sodium Pyrophosphate	D	D	D	D	D	A	C	C
	Sodium Resinate	D	D	D	D	D	A	C	C
	Sodium Salicylate	D	D	D	D	D	A	C	C
	Sodium Salts	D	D	D	D	D	A	A	A



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Sodium Sesquisilicate	D	D	D	D	D	D	D	D
	Sodium Silicate	A	A	A	A	A	A	A	A
	Sodium Silicofluoride	D	D	D	D	D	D	D	D
	Sodium Stannate	D	D	D	D	D	A	C	C
	Sodium Sulfate	A	B	A	A	A	A	A	A
	Sodium Sulfide	A	C	A	A	A	A	A	A
	Sodium Sulfite	A	A	A	A	A	A	A	A
	Sodium Sulfo cyanide	D	D	D	D	D	A	C	C
	Sodium Tartrate	D	D	D	D	D	A	C	C
	Sodium Tetraborate	A	D	D	D	D	A	C	C
	Sodium Tetraphosphate	D	D	D	D	D	A	C	C
	Sodium Tetrasulfide	D	D	D	D	D	A	C	C
	Sodium Thioarsenate	D	D	D	D	D	A	C	C
	Sodium Thiocyanate	D	D	D	D	D	A	C	C
	Sodium Thiosulfate	A	A	A	A	A	A	A	C
	Sodium Trichloroacetate	D	D	D	D	D	A	C	C
	Sodium Triphosphate	D	D	D	D	D	A	C	C
	Solution 555, 20% - Misc.	D	D	D	D	D	D	D	D
	Solvesso 100, 150	D	D	D	D	D	D	D	D
	Sorbitol	D	D	D	D	D	A	C	C
	Sour Crude Oil	D	D	D	D	D	C	A	C
	Sour Natural Gas	D	D	D	D	D	C	A	C
	Sovasol No. 1, 2, and 3	D	D	D	D	D	C	A	A
	Sovasol No. 73 and 74	D	D	D	D	D	C	A	B
	Soybean Oil	D	A	A	A	D	C	A	A
	Spry	D	D	D	D	D	B	A	A
	SR-10 Fuel	D	D	D	D	D	C	A	A
	SR-6 Fuel	D	D	D	D	D	C	A	B
	Standard Oil Mobilube GX90-EP Lube	D	D	D	D	D	C	A	A
	Stannic Ammonium Chloride	D	D	D	D	D	A	C	C
	Stannic Chloride	D	C	A	A	D	A	A	A
	Stannic Chloride, 50%	D	D	D	D	D	A	A	A
	Stannic Tetrachloride	D	D	D	D	D	A	C	C
	Stannous Bisulfate	D	D	D	D	D	A	C	C
	Stannous Bromide	D	D	D	D	D	A	C	C
	Stannous Chloride (15%)	D	D	D	D	D	A	A	A
	Stannous Fluoride	D	D	D	D	D	A	C	C
	Stannous Sulfate	D	D	D	D	D	A	C	C
	Stauffer 7700	D	D	D	D	D	C	A	B
	Steam Below 400°F	D	D	D	D	D	A	C	C
	Steam, 400°-500°F	D	D	D	D	D	C	C	C
	Steam, Above 500°F	D	D	D	D	D	D	D	D
	Stearic Acid	A	A	A	A	A	C	C	C
	Stoddard Solvent	D	A	A	A	D	C	A	A
	Strontium Acetate	D	D	D	D	D	A	C	C
	Strontium Carbonate	D	D	D	D	D	A	C	C
	Strontium Chloride	D	D	D	D	D	A	C	C
	Strontium Hydroxide	D	D	D	D	D	A	C	C
	Strontium Nitrate	D	D	D	D	D	A	C	C
	Styrene (Monomer)	D	A	A	A	A	C	C	C
	Succinic Acid	D	B	A	A	D	D	C	C
	Sucrose Solutions	A	A	A	A	D	A	A	A
	Sulfamic Acid	D	D	D	D	D	A	C	C
	Sulfanilic Acid	D	D	D	D	D	A	C	C
	Sulfanilic Chloride	D	D	D	D	D	C	A	B
	Sulfanilimide	D	D	D	D	D	C	A	B
	Sulfite Liquors	D	D	D	D	D	A	C	C
	Sulfolane	D	D	D	D	D	A	B	B
	Sulfonated Oils	D	D	D	D	D	C	A	B



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Sulfonic Acid	D	D	D	D	D	A	C	C
	Sulfonyl Chloride	D	D	D	D	D	A	C	C
	Sulfosalicylic Acid, pure - Acid, Organic, Aromatic	D	D	D	D	D	D	D	D
	Sulfur	D	D	D	D	A	A	A	C
	Sulfur (Molten)	D	D	D	D	D	C	A	C
	Sulfur Chloride	D	D	D	D	D	C	A	C
	Sulfur Dioxide, Dry	A	D	D	D	A	A	C	C
	Sulfur Dioxide, dry gas - Misc.	A	D	D	D	D	D	D	D
	Sulfur Dioxide, liquid - Misc.	A	D	D	D	D	D	D	D
	Sulfur Dioxide, Liquidified under pressure	D	D	D	D	D	A	C	C
	Sulfur Dioxide, pure - Misc.	A	D	D	D	D	D	D	D
	Sulfur Dioxide, Wet	A	B	A	A	D	A	C	C
	Sulfur Hexafluoride	D	D	D	D	D	A	C	B
	Sulfur Liquors	D	D	D	D	D	B	A	B
	Sulfur Monochloride	D	D	D	D	D	C	A	A
	Sulfur Salts, pure - Salt, Inorganic	C	D	D	D	D	D	D	D
	Sulfur Tetrafluoride	D	D	D	D	D	D	D	D
	Sulfur Trioxide Dry	D	D	D	D	A	B	A	C
	Sulfuric Acid (20% Oleum)	A	B	C	A	A	D	C	C
	Sulfuric Acid, 10% - Acid, Inorganic	A	C	A	A	D	C	A	C
	Sulfuric Acid, 100% - Acid, Inorganic	C	D	D	D	D	D	D	D
	Sulfuric Acid, 25% - Acid, Inorganic	A	C	A	A	D	C	D	C
	Sulfuric Acid, 2N - Acid, Inorganic	A	D	D	D	D	D	D	D
	Sulfuric Acid, 3 Molar to 158°F	D	D	D	D	A	A	A	B
	Sulfuric Acid, 30% - Acid, Inorganic	A	C	A	A	D	C	A	C
	Sulfuric Acid, 50% - Acid, Inorganic	B	C	A	A	D	C	A	C
	Sulfuric Acid, 6% - Acid, Inorganic	A	C	A	A	D	C	A	C
	Sulfuric Acid, 60% - Acid, Inorganic	B	C	A	A	D	C	A	C
	Sulfuric Acid, 6N - Acid, Inorganic	B	D	D	D	D	D	D	D
	Sulfuric Acid, 75% - Acid, Inorganic	C	C	A	A	D	C	A	C
	Sulfuric Acid, 96% - Acid, Inorganic	C	C	C	A	D	C	A	C
	Sulfuric Acid, 98% - Acid, Inorganic	C	C	C	A	D	C	A	C
	Sulfuric Acid, Concentrated Room Temp	C	C	C	A	A	C	A	C
	Sulfuric Acid, Concentrated to 158°F	C	D	D	D	A	C	A	C
	Sulfuric Acid, fuming - Acid, Inorganic	C	D	D	D	D	D	D	D
	Sulfuric Acid, pure - Acid, Inorganic	C	D	D	D	D	D	D	D
	Sulfuric Chlorohydrin (Chlorosulfonic Acid)	D	D	D	D	D	A	C	C
	Sulfurous Acid	A	B	A	A	A	C	A	C
	Sulfuryl Chloride, pure - Misc.	C	D	D	D	D	D	D	D
	Sunoco #3661	D	D	D	D	D	C	A	A
	Sunoco All purpose grease	D	D	D	D	D	C	A	A
	Sunoco SAE 10	D	D	D	D	D	C	A	A
	Sunsafe (Fire resist. hydr. fluid)	D	D	D	D	D	C	A	A
	Super Shell Gas	D	D	D	D	D	C	A	A
	Surfuryl Chloride	D	D	D	D	D	A	C	C
	Swan Finch EP Lube	D	D	D	D	D	C	A	A
	Swan Finch Hypoid-90	D	D	D	D	D	C	A	A
	sym-Trimethylbenzene, pure - Hydrocarbon, Aromatic	C	D	D	D	D	D	D	D
	Tallow	D	D	D	D	D	C	A	A
	Tannic Acid (10%)	D	A	A	A	A	A	A	A
	Tannic Acid, pure - Acid, Organic	A	A	A	A	D	A	A	A
	Tap Water - Misc.	A	A	A	A	D	A	A	A
	Tar, bituminous	D	A	A	A	A	D	A	B
	Tartaric Acid	A	A	A	A	A	C	A	A
	TCA, 10% - Acid, Organic, Halogenated	A	D	D	D	D	D	D	D
	TCA, 100% - Acid, Organic, Halogenated	B	D	D	D	D	D	D	D
	TCA, 25% - Acid, Organic, Halogenated	B	D	D	D	D	D	D	D
	TCA, pure - Acid, Organic, Halogenated	B	D	D	D	D	D	D	D
	Tellone II	D	D	D	D	D	D	D	D



Customer Tools

CATEGORY	DESCRIPTION									
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N	
A	No known effect									
B	Some effect, evaluate with caution									
C	Moderate to Severe effect, evaluation not recommended									
D	Unknown									
	Terephthalic Acid	D	D	D	D	D	A	C	C	C
	Terpineol	D	D	D	D	D	C	A	A	B
	Terpinyl Acetate	D	D	D	D	D	C	A	A	B
	tert-Butanol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D	D
	tert-Butanol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D	D
	tert-Butyl Alcohol, 100% - Alcohol, Aliphatic	A	D	D	D	D	D	D	D	D
	tert-Butyl Alcohol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D	D
	Tertiary Amyl Methyl Ether (TAME)	D	D	D	D	D	D	D	D	D
	Tertiary Butyl Catechol or p-Tert Butyl Catechol	D	D	D	D	D	B	A	A	C
	Tertiary Butyl Mercaptan	D	D	D	D	D	C	A	A	C
	Tetrabromoethane	D	D	D	D	D	C	A	A	C
	Tetrabromomethane	D	D	D	D	D	C	A	A	B
	Tetrabutyl Titanate	D	D	D	D	D	A	A	A	B
	Tetrachloroethylene	C	B	A	A	D	C	A	A	C
	Tetrachloroethane	D	C	A	A	D	C	A	A	C
	Tetraethyl Lead	D	B	A	A	D	C	A	A	C
	Tetraethyl Lead Blend	D	D	D	D	D	C	A	A	B
	Tetraethyl Orthosilicate (TEOS)	D	D	D	D	D	D	D	D	D
	Tetrahydrofuran	B	B	A	A	D	C	C	C	C
	Tetrahydronaphthalene, pure - Hydrocarbon, Aromatic	C	D	D	D	D	D	D	D	D
	Tetralin	C	D	D	D	D	C	A	A	C
	Tetramethyl Ammonium Hydroxide	D	D	D	D	D	A	C	A	C
	Tetramethylcyclotetrasiloxane (TMCTS)	D	D	D	D	D	D	D	D	D
	Tetramethyldihydropyridine	D	D	D	D	D	C	A	A	B
	Tetramethyldihydropyridine	D	D	D	D	D	C	A	A	B
	Tetraphosphoglucosate	D	D	D	D	D	A	C	A	C
	Tetraphosphoric Acid	D	D	D	D	D	D	D	D	D
	Texaco 3450 Gear Oil	D	D	D	D	D	C	A	A	A
	Texaco Capella A and AA	D	D	D	D	D	C	A	A	A
	Texaco Meropa 220 (No Lead)	D	D	D	D	D	C	A	A	A
	Texaco Regal B	D	D	D	D	D	C	A	A	A
	Texaco Uni-Temp Grease	D	D	D	D	D	C	A	A	A
	Texamatic A 1581 Fluid	D	D	D	D	D	C	A	A	A
	Texamatic A 3401 Fluid	D	D	D	D	D	C	A	A	A
	Texamatic A 3525 Fluid	D	D	D	D	D	C	A	A	A
	Texamatic A 3528 Fluid	D	D	D	D	D	C	A	A	A
	Texamatic A Transmission Oil	D	D	D	D	D	C	A	A	A
	Texas 1500 Oil	D	D	D	D	D	C	A	A	A
	TFA, 100% - Acid, Organic, Halogenated	D	D	D	D	D	D	D	D	D
	TFA, 20% - Acid, Organic, Halogenated	D	D	D	D	D	D	D	D	D
	TFA, 4% - Acid, Organic, Halogenated	A	D	D	D	D	D	D	D	D
	TFA, 48% - Acid, Organic, Halogenated	A	D	D	D	D	D	D	D	D
	TFA, pure - Acid, Organic, Halogenated	D	D	D	D	D	D	D	D	D
	Therminol 44	D	A	A	A	D	C	A	A	C
	Therminol 55	D	A	A	A	D	C	A	A	C
	Therminol 66	D	A	A	A	D	C	A	A	C
	Therminol FR	D	A	A	A	D	C	A	A	C
	Therminol VP-1, 60, 65	D	A	A	A	D	C	A	A	C
	THF, pure - Ether, Cyclic	B	D	D	D	D	D	D	D	D
	Thio Acid Chloride	D	D	D	D	D	D	D	D	D
	Thioamyl Alcohol	D	D	D	D	D	C	A	A	A
	Thiodiacetic Acid	D	D	D	D	D	A	C	A	C
	Thioethanol	D	D	D	D	D	A	C	A	C
	Thioglycolic Acid	D	D	D	D	D	A	C	A	C
	Thiokol TP-90B	D	D	D	D	D	A	A	A	C
	Thiokol TP-95	D	D	D	D	D	A	A	A	C
	Thionyl Chloride	C	D	D	D	D	C	A	A	B
	Thiophene (Thiofuran)	D	D	D	D	D	C	A	A	B
	Thiophosphoryl Chloride	D	D	D	D	D	A	C	A	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Thiourea	D	D	D	D	D	A	C	C
	Thorium Nitrate	D	D	D	D	D	A	C	C
	Tidewater Multigear, 140 EP Lube	D	D	D	D	D	C	A	A
	Tidewater Oil-Beedol	D	D	D	D	D	C	A	A
	Tin Ammonium Chloride	D	D	D	D	D	A	C	C
	Tin Chloride	D	D	D	D	D	C	A	A
	Tin Tetrachloride	D	D	D	D	D	C	A	A
	Tincture of Iodine - Misc.	A	D	D	D	D	D	D	D
	Titanic Acid	D	D	D	D	D	A	C	C
	Titanium Dioxide	D	A	A	A	D	A	D	D
	Titanium Sulfate	D	D	D	D	D	A	C	C
	Titanium Tetrachloride	D	B	A	A	D	C	A	C
	Toluene	C	A	A	A	A	C	D	C
	Toluene Bisodium Sulfite	D	D	D	D	D	D	D	D
	Toluene Diisocyanate (TDI)	D	D	D	D	D	B	C	C
	Toluene Sulfonyl Chloride	D	D	D	D	D	C	A	B
	Toluenesulfonic Acid	D	D	D	D	D	A	C	C
	Toluidine	D	D	D	D	D	C	A	B
	Toluol	C	D	D	D	A	A	C	C
	Toluquinone	D	D	D	D	D	C	A	B
	Tolylaldehyde	D	D	D	D	D	A	C	C
	Transformer Oil	A	D	D	D	D	C	A	A
	Transmission Fluid Type A	D	A	A	A	D	C	A	A
	Triacetin	D	D	D	D	D	A	C	B
	Triaryl Phosphate	D	D	D	D	D	A	A	C
	Tribasic Potassium Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Tribromomethylbenzene	D	D	D	D	D	C	A	B
	Tributoxyethyl Phosphate	D	D	D	D	D	A	A	C
	Tributyl Citrate	B	D	D	D	D	A	C	C
	Tributyl Mercaptan	D	D	D	D	D	C	A	C
	Tributyl Phosphate	D	D	D	D	A	A	C	C
	Tributylamine	D	D	D	D	D	D	D	D
	Trichloroacetic Acid	B	C	A	A	D	C	C	C
	Trichloroacetyl Chloride	D	D	D	D	D	C	A	B
	Trichlorobenzene	C	A	A	A	D	C	A	C
	Trichloroethane	C	A	A	A	D	C	A	C
	Trichloroethanolamine	C	D	D	D	D	A	C	C
	Trichloroethylene	C	A	A	A	D	C	A	C
	Trichlorofluoromethane, pure - Hydrocarbon, Aliphatic, Halogenated	D	D	D	D	D	D	D	D
	Trichloromethane	D	D	D	D	D	C	A	C
	Trichloronitromethane (Chloropicrin)	D	D	D	D	D	A	C	C
	Trichlorophenylsilane	D	D	D	D	D	D	D	D
	Trichloropropane	D	D	D	D	D	C	A	C
	Trichlorosilane	D	D	D	D	D	C	A	C
	Trichlorotrifluoroethane, pure - Hydrocarbon, Aliphatic, Halogenated	A	D	D	D	D	D	D	D
	Tricresyl Phosphate	A	D	D	D	D	A	B	C
	Triethanol Amine	D	A	A	A	D	C	C	C
	Triethanolamine, pure - Amine, Aliphatic	C	A	A	A	D	C	C	C
	Triethyl Phosphate	D	D	D	D	D	C	A	B
	Triethylaluminum	D	D	D	D	D	D	D	D
	Triethylamine, pure - Amine, Aliphatic	D	D	D	D	D	D	D	D
	Triethylborane	D	D	D	D	D	D	D	D
	Triethylene Glycol	D	D	D	D	D	A	C	C
	Triethylene Glycol, pure - Alcohol, Aliphatic, Polyol	A	D	D	D	D	D	D	D
	Triethylenetetramine	D	D	D	D	D	A	C	C
	Trifluoroacetic Acid	D	D	D	D	D	A	C	C
	Trifluoroethane	D	D	D	D	D	C	A	C
	Trifluoromethane	D	D	D	D	D	C	A	C
	Trifluorovinylchloride	D	D	D	D	D	C	A	B



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
A	No known effect								
B	Some effect, evaluate with caution								
C	Moderate to Severe effect, evaluation not recommended								
D	Unknown								
	Triisopropylbenzylchloride	D	D	D	D	D	C	A	B
	Trimethylamine	D	D	D	D	D	A	C	C
	Trimethylamine (TMA)	D	D	D	D	D	A	C	C
	Trimethylamine, pure - Amine, Aliphatic	B	D	D	D	D	D	D	D
	Trimethylbenzene	C	D	D	D	D	C	A	B
	Trimethylborate (TMB)	D	D	D	D	D	C	A	B
	Trimethylpentane	C	D	D	D	D	C	A	A
	Trinitrotoluene (TNT)	D	D	D	D	D	C	B	C
	Trioctyl Phosphate	D	D	D	D	D	A	B	C
	Triphenylphosphite	D	D	D	D	D	A	C	C
	Tripoly Phosphate	D	D	D	D	D	A	B	C
	Tripotassium Phosphate	A	D	D	D	D	A	C	C
	Tripotassium Phosphate, pure - Salt, Inorganic	A	D	D	D	D	D	D	D
	Tripropylene Glycol, pure - Alcohol, Aliphatic, Polyol	A	D	D	D	D	D	D	D
	Tris Buffer Solution, pure - Misc.	A	D	D	D	D	D	D	D
	Trisodium Phosphate	A	D	D	D	D	A	C	C
	Tritium	D	D	D	D	D	D	D	D
	Triton X-100, pure - Detergent	D	D	D	D	D	D	D	D
	TSP, pure - Base/Caustic, Inorganic	A	D	D	D	D	D	D	D
	Tung Oil (China Wood Oil)	D	A	A	A	A	C	A	A
	Tungsten Hexafluoride	D	D	D	D	D	D	D	D
	Tungstic Acid	D	D	D	D	D	D	D	D
	Turbine Oil	D	D	D	D	D	C	A	A
	Turbine Oil #15 (MIL-L-7808A)	D	D	D	D	D	C	A	B
	Turbo Oil #35	D	D	D	D	D	C	A	A
	Turpentine	C	A	A	A	A	C	A	A
	Type I Fuel (MIL-S-3136)(ASTM Ref. Fuel A)	D	D	D	D	D	C	A	A
	Type II Fuel MIL-S-3136	D	D	D	D	D	C	A	B
	Type III Fuel MIL-S-3136(ASTM Ref. Fuel B)	D	D	D	D	D	C	A	B
	Ucon Hydrolube J-4	D	D	D	D	D	A	A	A
	Ucon Lubricant 50-HB-100	D	D	D	D	D	A	A	A
	Ucon Lubricant 50-HB-260	D	D	D	D	D	A	A	A
	Ucon Lubricant 50-HB-5100	D	D	D	D	D	A	A	A
	Ucon Lubricant 50-HB55	D	D	D	D	D	A	A	A
	Ucon Lubricant 50-HB-660	D	D	D	D	D	A	A	A
	Ucon Lubricant LB-1145	D	D	D	D	D	A	A	A
	Ucon Lubricant LB-135	D	D	D	D	D	A	A	A
	Ucon Lubricant LB-285	D	D	D	D	D	A	A	A
	Ucon Lubricant LB-300X	D	D	D	D	D	A	A	A
	Ucon Lubricant LB-625	D	D	D	D	D	A	A	A
	Ucon Lubricant LB-65	D	D	D	D	D	A	A	A
	Ucon Oil 50-HB-280x	D	A	A	A	D	A	D	B
	Ucon Oil Heat Transfer 500(Polyalkalene Glycol)	D	A	A	A	D	A	A	A
	Ucon Oil LB-385	D	A	A	A	D	A	A	A
	Ucon Oil LB-400X	D	A	A	A	D	A	A	A
	Undecyl Alcohol, pure - Alcohol, Aliphatic	A	D	D	D	D	D	D	D
	Undecylenic Acid	D	D	D	D	D	C	A	B
	Undecylic Acid	D	D	D	D	D	C	A	B
	Univis 40 (Hydr. Fluid)	D	D	D	D	D	C	A	A
	Univolt #35 (Mineral Oil)	D	D	D	D	A	C	A	A
	Unsymmetrical Dimethyl Hydrazine (UDMH)	D	D	D	D	D	A	C	B
	UPDI(Ultrapurpure Deionized Water)	D	D	D	D	D	A	C	C
	Uranium Hexachloride	D	D	D	D	D	D	A	D
	Uranium Hexafluoride	D	D	D	D	D	D	D	D
	Uranium Sulfate	D	D	D	D	D	D	D	D
	Urea, pure - Amine, Aliphatic	A	B	A	A	D	C	C	C
	Uric Acid	D	D	D	D	D	A	C	C
	Urine - Misc.	A	D	D	D	D	D	D	D
	Valeraldehyde	D	D	D	D	D	A	C	C



Customer Tools

CATEGORY	DESCRIPTION								
		Polypropylene	316SS	Carbon	Ceramic	PTFE (Teflon-type)	Fluorocarbon (Viton-type)	EPDM	Nitrile / Buna N
	Valeric Acid	D	D	D	D	D	A	C	C
	Vanadium Oxide	D	D	D	D	D	C	A	A
	Vanadium Pentoxide	D	D	D	D	D	C	A	A
	Varnish	D	D	D	D	A	C	A	B
	Vegetable Oil	A	A	A	A	D	C	A	A
	Versilube F44, F55	D	D	D	D	D	A	A	A
	Versilube F-50	D	D	D	D	D	A	A	A
	Vinegar	A	A	A	A	A	C	C	C
	Vinyl Acetate	D	A	A	A	D	D	C	C
	Vinyl Benzene	D	D	D	D	D	C	A	B
	Vinyl Benzoate	D	D	D	D	D	C	A	B
	Vinyl Chloride	D	A	A	A	D	C	A	C
	Vinyl Fluoride	D	D	D	D	D	C	A	B
	Vinylidene Chloride	C	D	D	D	D	C	A	B
	Vinylpyridine	D	D	D	D	D	C	A	B
	Vitriol (White)	D	D	D	D	D	A	C	C
	VV-H-910	D	D	D	D	D	A	A	C
	Wagner 21B Brake Fluid	D	D	D	D	D	A	C	C
	Water	A	A	A	A	A	A	A	A
	Waycoat 59 Photoresist - Misc., Photoresist	D	D	D	D	D	D	D	D
	Wemco C	D	D	D	D	D	C	A	A
	Whiskey	D	A	A	A	A	A	D	D
	White Liquor	D	D	D	D	D	A	A	A
	White Oil	D	D	D	D	D	C	A	A
	White Paraffin, pure - Hydrocarbon, Mixture	B	D	D	D	D	D	D	D
	White Pine Oil	D	D	D	D	D	C	A	B
	White Spirits - Hydrocarbon, Mixture	D	D	D	D	D	D	D	D
	Wine	D	A	A	A	A	A	A	A
	Wolmar Salt	D	D	D	D	D	A	A	A
	Wood Alcohol	D	D	D	D	D	A	C	A
	Wood Oil	D	D	D	D	D	C	A	A
	Xenon	D	D	D	D	D	A	A	A
	Xylene	C	A	A	A	A	C	A	C
	Xylidenes-Mixed-Aromatic Amines	D	D	D	D	D	A	C	C
	Xylol	C	D	D	D	A	C	A	C
	Zeolites	D	D	D	D	D	A	A	A
	Zephiran Chloride, 1% - Misc., Disinfectant	A	D	D	D	D	D	D	D
	Zephiran Chloride, 7% - Misc., Disinfectant	A	D	D	D	D	D	D	D
	Zinc Acetate	D	D	D	D	D	A	C	B
	Zinc Ammonium Chloride	D	D	D	D	D	A	C	C
	Zinc Chloride	A	C	A	A	A	A	A	A
	Zinc Chromate	D	D	D	D	D	A	C	C
	Zinc Cyanide	D	B	A	A	D	A	D	D
	Zinc Diethyldithiocarbamate	D	D	D	D	D	A	C	C
	Zinc Dihydrogen Phosphate	D	D	D	D	D	A	C	C
	Zinc Fluorosilicate	D	D	D	D	D	D	D	D
	Zinc Hydrosulfite	D	D	D	D	D	A	C	C
	Zinc Naphthenate	D	D	D	D	D	D	D	D
	Zinc Nitrate	D	B	A	A	D	A	A	A
	Zinc Oxide	D	D	D	D	D	A	A	A
	Zinc Phenolsulfonate	D	D	D	D	D	A	C	C
	Zinc Phosphate	D	A	A	A	D	A	A	A
	Zinc Salts	D	D	D	D	D	A	A	A
	Zinc Silicofluoride	D	D	D	D	D	D	D	D
	Zinc Stearate	A	D	D	D	D	A	C	C
	Zinc Sulfate	A	B	A	A	A	A	A	A
	Zinc Sulfide	D	D	D	D	D	A	C	C
	Zirconium Nitrate	D	D	D	D	D	A	A	A